

SURFACE PREPARATION

Surfaces must be clean and free of dirt, oil, excessive chalk, or any other contaminants that may prevent proper adhesion. New masonry surfaces should be allowed to cure for at least 7 days before applying GRIP TITE. Pressure wash surfaces to ensure that all curing and form release agents have been removed. Fill all voids, cracks and any other surface defects with the appropriate exterior sealants and patches. To insure proper adhesion, plaster surfaces need to be inspected for dust or powder that may be present on the surface upon drying. If present, walls should be washed with a solution consisting of 1-pint household vinegar to 1-gallon of water. Repeat until surface is free of powder. Rinse with clear water and allow to dry. Contact your sales representative or contact the closest **hallman/lindsay** store for specific recommendations. In severe cases, unusually slick, poured or precast concrete should be acid etched or sandblasted. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

hallman/lindsay FINISH RECOMMENDATIONS

Latex Interior: Choose any appropriate **hallman/lindsay** topcoat.
Latex Exterior: Choose any appropriate **hallman/lindsay** topcoat.

APPLICATION

Mix thoroughly before use. Apply by brush, roller or airless or conventional spray. If sprayed, product should be back-rolled or brushed to properly work into surface. Apply when the ambient, surface, and material temperatures 50° F or higher. DO NOT APPLY IN DIRECT SUNLIGHT. Thinning is not recommended.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum 1/2 GPM with .019" tip @ 2700 PSI
- ✓ Conventional: Binks #7 gun, 38 needle, 36 air nozzle, 38 fluid nozzle 9.3 CFM @ 30PSI
- ✓ HVLP: Twin Stage Turbine, 5-8 PSI, .051 to .070 projector set
- ✓ Roller: ½" - 1½" nap synthetic cover, depending on surface
- ✓ Brush: Quality nylon /polyester brush



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ① FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.