

SURFACE PREPARATION

SURFACE PREPARATION: Surfaces must be clean and free of dirt, oil, excessive chalk, or any other contaminants that may prevent proper adhesion. New masonry surfaces should be allowed to cure for at least 7 days before applying. Pressure wash surfaces to ensure that all curing and form release agents have been removed. Allow to dry. Fill all voids, cracks and any other surface defects with the appropriate exterior sealants and patches. Contact your sales representative or the closest hallman/lindsay store for specific recommendations. In severe cases, i.e. unusually slick poured or precast concrete, acid etch or sandblast.

WARNING! If you scrape sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Self Priming : 2 coats minimum over un-primed or finished surface

Mix thoroughly before use. Apply by brush, roller for small surfaces (when spraying is not an option) or airless spray (preferred). If sprayed, product should be back-rolled or brushed to properly work into surface. Apply when the ambient, surface, and material temperatures 50° F or higher. **DO NOT APPLY IN DIRECT SUNLIGHT.** Thinning is not recommended.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum 1 GPM with .017- .021" tip @ 2000 PSI
- ✓ Roller: 3/8" – 1/2" nap synthetic cover, depending on surface
- ✓ Brush: Quality nylon /polyester brush



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.