



# PRODUCT DATA SHEET

## KRIL FILL

### 100% ACRYLIC SATIN FILL & FINISH

#### 182-1

#### DESCRIPTION

hallman/lindsay's *ProSeries* is our full line of finishes designed for the professional contractor.

KRIL FILL 100% ACRYLIC SATIN FILL & FINISH is designed as a 100% acrylic fill and finish, single-use product for interior and exterior masonry surfaces.

The satin finish provides for low dirt pick-up, and the 100% acrylic formulation affords the owner with outstanding color and gloss retention, along with mildew resistance and moisture protection.

Intended for use on new and previously painted interior and exterior masonry surfaces. Two coats properly applied will give the owner a pinhole-free finish without having to use multiple products.

#### FEATURES

- ✓ 100% Acrylic
- ✓ Low Dirt Pick-Up
- ✓ High Film Build
- ✓ Easy Application
- ✓ Fill and Finish with Same Product
- ✓ Mildew- and Moisture-Resistant
- ✓ Washable
- ✓ Interior and Exterior Applications

#### PERFORMANCE DATA

- ✓ Performance alternate for Federal Paint Specification TT-P-25 F

#### PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Not suited for areas of extreme hydrostatic pressure. Not intended as a below-grade waterproofing system.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

#### TECHNICAL SERVICES

#### TECHNICAL DATA

- ✓ Color/Tinting:  
Pro White. May be tinted, up to 2 oz. per gallon, with low VOC colorants.
- ✓ Vehicle Type:  
100% Acrylic
- ✓ Gloss: Satin  
25-35 units @ 60°  
Gloss may vary depending upon porosity and texture of masonry surface.
- ✓ Percent Solids:  
Weight: 53% ± 2  
Volume: 42% ± 2
- ✓ Recommended Spreading Rate:  
Apply at 80-100 sq.ft./gal. to achieve  
15-20 mils Wet Film Thickness  
6-8 mils Dry Film Thickness  
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Drying Time at 77°F 50% R.H.:  
To touch: 1 hour  
Recoat: Overnight  
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
- ✓ Thinning/Cleanup:  
Water
- ✓ VOC:  
111 g/L      0.92 lbs. /gal.

Products of Hallman/Lindsay Paints  
Sun Prairie, WI 53590

9 Finishes  
Painting (09900)



**FACTORY & MAIN OFFICES**  
Ph. 608/834-8844  
Fax 608/837-1064  
[www.hallmanlindsay.com](http://www.hallmanlindsay.com)

Rev. 3/18

## **SURFACE PREPARATION**

Surfaces must be dry, clean, and free of dust, dirt, grease, soap or powdery residue, mortar splatter, loosely adhering paints or any other contaminants. Mortar joints must be raked clean of any loose material before finishing. Fill cracks, holes and other surface defects with proper patching materials and dull glossy surfaces by sanding. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

## **hallman/lindsay PRIMER RECOMMENDATIONS**

### **NEW WORK**

Rough Masonry, Brick:	Self-priming, (requires 2 coats) or 179 or 181
Rough Masonry, Concrete Block:	Self-priming, (requires 2 coats) or 179 or 181
Smooth Masonry, Pre-Cast, Tilt-Up:	Self-priming, (requires 2 coats) or 166

### **REPAINT WORK**

All surfaces: Spot prime all bare areas with suitable primer

## **hallman/lindsay FINISH RECOMMENDATIONS**

One or two coats of 182-1.

## **APPLICATION**

Mix thoroughly before use. Designed for airless spray application. To achieve optimum performance from coating, apply two (2) coats of 182-1 at 80–100 sq.ft. per gallon. Spray and backroll both applications, pushing the coating into the surface. May also be brushed and rolled. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Surfaces should be dry prior to paint application.

## **EQUIPMENT REQUIREMENTS**

- ✓ Airless: Minimum 1 GPM with .025" tip @ 2500 PSI
- ✓ Conventional: Not recommended
- ✓ HVLP: Not recommended
- ✓ Roller: ½"-1" nap shed-resistant or lambswool cover
- ✓ Brush: 100% nylon or synthetic blend



### **FACTORY & MAIN OFFICES**

1717 N. Bristol Street ☒ Sun Prairie, WI 53590  
☎ (608) 834-8844 ① FAX (608) 837-1064 🌐 [www.hallmanlindsay.com](http://www.hallmanlindsay.com)

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.