



PRODUCT DATA SHEET

FARM & RANCH ALKYD OIL BARN PAINT 200

DESCRIPTION

FARM & RANCH ALKYD OIL BARN PAINT is a quality, red exterior linseed oil paint developed specifically for use on farm structures. It has excellent durability, color retention and an attractive semi-gloss finish. .

Use on most new or previously painted exterior surfaces typically found on a farm — wood, properly primed masonry and properly primed metal.

FEATURES

- ✓ High Solids/Film Build
- ✓ Penetrates and Protects
- ✓ Self Priming
- ✓ Excellent Durability
- ✓ Improved Adhesion to Marginal Surface

PRECAUTIONS/LIMITATIONS

- ✓ Contains linseed oil. Rags or clothing soaked with this product should be immersed entirely in water until disposal to prevent spontaneous combustion.
- ✓ Please refer to Safety Data Sheets.
- ✓ Allow for overnight dry prior to topcoating.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL DATA

- ✓ Color/Tinting:
Red. Do not tint.
- ✓ Vehicle Type:
Oil/Alkyd
- ✓ Gloss: Satin
25-35 units @ 60°
- ✓ Percent Solids:
Weight: 83% ± 2
Volume: 69% ± 2
- ✓ Recommended Spreading Rate:
Apply at 430 sq. ft./gal. to achieve
3.0 mils Wet Film Thickness
2.0 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique,
- ✓ Drying Time at 77° F 50% R.H.:
To touch: 12-16 hours
Recoat: Overnight
- ✓ Thinning/Cleanup:
Mineral Spirits
- ✓ VOC/Package:
236 g/L 1.98 lbs./gal

Products of Hallman/Lindsay Paints
Sun Prairie, WI 53590

9
Finishes
Painting (09900)

TECHNICAL SERVICES



FACTORY & MAIN OFFICES

Ph. 608/834-8844

Fax 608/837-1064

www.hallmanlindsay.com

Rev. 3/18

SURFACE PREPARATION

Surfaces must be dry, clean and free of dirt, oil, chalk, rust or any other contaminants that may prevent proper adhesion. Remove all loose, scaling or peeling paint by power washing, scraping and/or wire brushing. Glossy surfaces should be dulled by sanding. Patch all holes and cracks with appropriate patching compound and sand smooth. Sand all leading edges on bare spots.

PRIMING RECOMMENDATIONS

Wood:	Self priming (requires 2 coats) or one coat 111
Metal, Ferrous (Steel):	One coat 330
Metal, Non-ferrous (Aluminum, Galvanized):	One coat 338

REPAINT WORK

Primer: Spot-prime all bare areas with suitable primer

FINISH

One or two coats 200

APPLICATION

Mix thoroughly before use. Apply by brush, roller, airless, HVLP or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Surfaces should be dry prior to paint application.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum $\frac{3}{4}$ " GPM with .019" tip @ 2500 PSI
- ✓ Conventional: Binks #7 gun, 38 needle, 36 air nozzle, 38 fluid nozzle, 9.3 CFM @ 30 PSI
- ✓ HVLP: Twin-stage turbine, 5 – 8 PSI, .051 to .070 projector set
- ✓ Roller: 3/8" – 3/4" shed-resistant cover or lambswool cover
- ✓ Brush: Natural china bristle or synthetic blend



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 ☎ www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.