



# PRODUCT DATA SHEET

## FARM & RANCH

### ACRYLIC FLAT EXTERIOR

# 202

#### DESCRIPTION

hallman/lindsay's *ProSeries* is our full line of finishes designed for the professional contractor.

FARM AND RANCH is a high-hiding, premium acrylic-alkyd exterior finish providing outstanding adhesion, color retention, durability and chalking resistance.

FARM AND RANCH is designed for use on new or previously painted wood, masonry or properly primed metals.

#### FEATURES

- ✓ Excellent Adhesion
- ✓ High-Hiding
- ✓ Resists Chalking
- ✓ Durable
- ✓ Easy Soap and Water Clean-up

#### PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

#### TECHNICAL DATA

- ✓ Color/Tinting:  
White. May be tinted
- ✓ Vehicle Type:  
Acrylic-Alkyd
- ✓ Gloss: Flat  
2-6 units @ 60°
- ✓ Percent Solids by Weight:  
Weight: 55% ± 2  
Volume: 38% ± 2
- ✓ Recommended Spreading Rate:  
Apply at 400 sq.ft./gal. to achieve  
4.0 mils Wet Film Thickness  
1.5 mils Dry Film Thickness  
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Drying Time at 77° F 50% R.H.:  
To touch: 1 hour  
Recoat: 2 hours  
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
- ✓ Cleanup:  
Water
- ✓ VOC:  
25 g/L                      0.20 lb./gal.

Products of Hallman/Lindsay Paints  
Sun Prairie, WI 53590

9  
Finishes  
Painting (09900)

## TECHNICAL SERVICES



#### FACTORY & MAIN OFFICES

Ph. 608/834-8844

Fax 608/837-1064

[www.hallmanlindsay.com](http://www.hallmanlindsay.com)

Rev. 3/18

## SURFACE PREPARATION

Surfaces must be dry, clean and free of dirt, oil, chalk, rust or any other contaminants that may prevent proper adhesion. Remove all loose, scaling or peeling paint by power washing, scraping and/or wire brushing. Glossy surfaces should be dulled by sanding. Bare metal and raw wood must be primed. Patch all holes and cracks with appropriate patching compound and sand smooth. Galvanized surfaces shall have all oils removed prior to application of coating. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

## hallman/lindsay PRIMER RECOMMENDATIONS

Wood:	Self-Priming (requires 2 coats) 111 or 112
Metal, Ferrous (Steel):	One coat 330 or 338
Metal, Non-ferrous (Galvanized):	One coat 338
Rough Masonry/Concrete Block:	One coat 181
Smooth Masonry/Brick:	Self-priming (requires 2 coats) 112 or 166

## hallman/lindsay FINISH RECOMMENDATIONS

One or two coats 202

## APPLICATION

Mix thoroughly before use. Apply by brush, roller or airless spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Surfaces should be dry prior to paint application.

## EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum ¾ GPM, .017" tip @ 2500 PSI
- ✓ Conventional: Not recommended
- ✓ HVLP: Not recommended
- ✓ Roller: ½"-1" nap synthetic cover
- ✓ Brush: 100% nylon or synthetic blend



### FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590  
☎ (608) 834-8844 ☎ FAX (608) 837-1064 ☎ [www.hallmanlindsay.com](http://www.hallmanlindsay.com)

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.