



PRODUCT DATA SHEET

WALL PREP

PREMIUM WALL PRIMER/SEALER

226-1

DESCRIPTION

hallman/lindsay's **Builders Legacy** is our finest line of finishes designed for new drywall surfaces. All of our **Builders Legacy** products meet LEEDS criteria for new construction.

WALL PREP PREMIUM WALL PRIMER/SEALER is a top-line professional primer/sealer for unpainted drywall. It can be used under a wide range of finishes but it's higher sheen and superior sealing properties make it an excellent choice under Eggshell, Satin and Semi-Gloss finishes for new construction in the residential, multi-family, commercial and institutional markets.

FEATURES

- ✓ Meets criteria set forth by the U.S. Green Building Council LEED-NC, version 2.2 and LEED-CI version 2.0.
- ✓ Higher Sheen
- ✓ Excellent Sealing Properties
- ✓ High Hiding
- ✓ Excellent Coverage
- ✓ Quick-Dry
- ✓ Low-Odor
- ✓ Zero VOC per EPA Method 24
- ✓ **NOTE:** Material VOC content at or below 5g/L. This is based on an interpretation of the SCAQMD Rule 314 exemption for "Zero VOC equivalent" coatings.

PERFORMANCE DATA

Performance alternate for Federal Paint Specification TT-P-650 D

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Do not apply to "hot" plaster.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL DATA

- ✓ Color/Tinting:
Pro White. May be tinted with up to 4 ounces of low VOC universal colorants.
- ✓ Vehicle Type:
Ethylene-Vinyl Acetate
- ✓ Gloss
25% @ 85°
- ✓ Percent Solids by Weight:
41% ± 2
- ✓ Percent Solids by Volume:
27% ± 2
- ✓ Pigment by Weight:
33% ± 2
- ✓ Vehicle Solids by Weight
8% ± 2
- ✓ Recommended Spreading Rate:
Apply at 300-350 sq.ft./gal to achieve
4.5–5.3 mils Wet Film Thickness
1.2–1.4 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Weight per Gallon:
10.65 lbs.
- ✓ Drying Time at 77°F 50% R.H.:
To touch: 1 hour
Recoat: 2 hours
- ✓ Thinning/Cleanup:
Water
- ✓ VOC (EPA Method 24):
0 g/L 0 lbs./gal

Products of Hallman/Lindsay Paints
Sun Prairie, WI 53590

9 Finishes
Painting (09900)

TECHNICAL SERVICES



FACTORY & MAIN OFFICES
Ph. 608/834-8844
Fax 608/837-1064
www.hallmanlindsay.com

SURFACE PREPARATION

On drywall, all taped joints and nail heads should be sanded smooth and dusted. Patch all holes and cracks with an appropriate patching compound. Let dry thoroughly, sand smooth and prime. Surfaces must be dry, clean and free of dirt, oil or any other contaminants.

hallman/lindsay FINISH RECOMMENDATIONS

Excellent choice under Eggshell, Satin and Semi-Gloss finishes. May be used as a primer under appropriate hallman/lindsay top coats.

SPECIFICATION

None

APPLICATION

Mix thoroughly before use. Apply by brush, roller, airless, HVLP or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Surfaces should be dry prior to paint application. Reducing material for spray application should not exceed 10%.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum ½ GPM with .017" tip @ 2000 PSI
- ✓ Conventional: Binks #7 gun, 38 needle, 36 air nozzle, 38 fluid nozzle, 9.3 CFM @ 30 PSI
- ✓ HVLP: Twin-stage turbine, 5–8 PSI, .051 to .070 projector set
- ✓ Roller: ¼" – ½" nap shed-7resistant cover or lambs wool cover
- ✓ Brush: 100% nylon or synthetic blend



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.