



PRODUCT DATA SHEET

DROP DRY ALKYD INTERIOR

242

DESCRIPTION

hallman/lindsay's *ProSeries* is our full line of finishes designed for the professional contractor.

DROP DRY ALKYD EGGSHELL INTERIOR is a high-quality, drop dry solvent finish designed for use on ceiling surfaces where adhesion and reflectance are the major performance requirements. The Deck White color was developed to match insulation.

Formulated with higher levels of titanium dioxide than standard dry fogs, DROP DRY has better wet hide than the competition, which provides for improved square foot coverage rates. The eggshell finish resists dirt pick-up.

Intended for use in commercial/industrial facilities, such as new, primed or existing structural steel ceilings, supports and I-beams. Can be used on properly primed or previously painted concrete/drywall.

FEATURES

- ✓ Fast Dry (10 Foot Drop Dry)
- ✓ Easy Sweep-Up
- ✓ High Reflectance Levels
- ✓ Outstanding Square Foot Coverage Rates
- ✓ Excellent Adhesion
- ✓ Resists Dirt Pick-Up

PERFORMANCE DATA

- ✓ Approved Master Painters Institute (MPI)
Category # 89

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Do not apply to non-primed aluminum or galvanized metal.
- ✓ Not for use on foil or vinyl backed insulation.
- ✓ For interior application only.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL DATA

- ✓ Color/Tinting:
Deck White. May be tinted, up to 2 oz. per gallon, with most universal colorants.
- ✓ Vehicle Type:
Alkyd
- ✓ Gloss: Eggshell
15-25 units @ 60°
- ✓ Percent Solids:
Weight: 54% ± 2
Volume: 35% ± 2
- ✓ Recommended Spreading Rate:
Apply at 400 sq. ft./gal. to achieve
4.0 mils Wet Film Thickness
1.9 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Drying Time at 77°F 50% R.H.:
To touch: 15 minutes
Recoat: 4 hours
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
- Thinning:
Do not thin.
- ✓ Cleanup:
VM&P Naphtha.
- ✓ VOC:
394 g/L 3.29 lb./gal.

TECHNICAL SERVICES



FACTORY & MAIN OFFICES

Ph. 608/834-8844

Fax 608/837-1064

www.hallmanlindsay.com

Rev. 3/18

SURFACE PREPARATION

Surfaces must be dry, clean and free of dirt, oil, chalk, rust or any other contaminants that may prevent proper adhesion. Remove all loose or peeling paint. Glossy surfaces must be dulled by sanding. Do not apply over rusty surfaces. Ferrous metals should be hand tooled clean (SSPC-SP-2) to remove rust and corrosion, followed by spot priming. Galvanized surfaces shall have all oils removed prior to application of coating. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

hallman/lindsay PRIMER RECOMMENDATIONS

NEW WORK

Wood:	One coat 231
Rough Masonry/Concrete Block:	One coat 181 or 184
Smooth Masonry/Brick:	One coat 166
Plaster:	One coat 166
Metal, Ferrous (Steel):	One coat 330
Metal, Non-ferrous (Galvanized):	One coat 338
Drywall:	Self-priming (requires 2 coats) or 220

REPAINT WORK

Spot prime using suitable primer as listed above

hallman/lindsay FINISH RECOMMENDATIONS

One or two coats 242

APPLICATION

Apply by airless spray application. Surfaces should be dry prior to paint application. Low temperatures or increased humidity will affect drying levels. Test application should be provided to determine if satisfactory levels are being attained.

EQUIPMENT REQUIREMENTS

✓ Airless: Minimum 1 GPM, .021" tip @ 2500 PSI



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 ☎ www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.