



PRODUCT DATA SHEET

LUSTRE KOTE

280

DESCRIPTION

Hallman/Lindsay's Lustre Kote is a premium 100% acrylic interior wall paint. Formulated for an easy to apply, smooth finish, Lustre Kote has outstanding hide and durability, as well as superior stain and moisture resistance.

Use on a variety of surfaces including drywall, plaster, wood, primed metals and masonry. The 100% acrylic resin formula exhibits strong adhesive properties.

Ideal for areas that are subject to heavy traffic, abuse and soil: offices, hallways, baths, kitchens, and classrooms. Exhibits excellent hiding, flow and leveling, and has a tough scrubbable finish, yet maintains a rich lo-sheen appearance

FEATURES

- ✓ Water Resistant Acrylic
- ✓ Excellent Stain Resistance
- ✓ Durable/Scrub Resistant
- ✓ High-Hiding
- ✓ Smooth, Easy to Apply
- ✓ Spatter Resistant Formula
- ✓ Anti-Microbial

PERFORMANCE DATA

- ✓ **Meets criteria set forth by the U.S. Green Building Council LEED-NC, version 2.2 and LEED-CI version 2.0.**
- ✓ Performance alternate for Federal Paint Specification TT-P-2119 (class 2)
- ✓ Performance alternate (MPI) Category #44

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL SERVICES



FACTORY & MAIN OFFICES
 Ph. 608/834-8844
 Fax 608/837-1064
www.hallmanlindsay.com

TECHNICAL DATA

- ✓ Color/Tinting:
White and tint bases.
- ✓ Vehicle Type:
100% Acrylic
- ✓ Gloss: Lo-Sheen
5 units @ 60°
15-20 units @ 85°
- ✓ Percent Solids:
Weight: 54% ± 2
Volume: 40% ± 2
- ✓ Recommended Spreading Rate:
Apply at 400 sq.ft./gal. to achieve
4.0 mils Wet Film Thickness
1.6 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Drying Time at 77°F 50% R.H.:
To touch: 1 hour
Recoat: 4 hours
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
- ✓ Thinning/Cleanup:
Water
- ✓ VOC:
46 g/L 0.38 lb./gal.

SURFACE PREPARATION

Surfaces must be dry, clean and free of dirt, oil, grease, wax, dust, chalk, rust or any other contaminants that may prevent proper adhesion. Remove all loose or peeling paint. Glossy surfaces must be dulled by sanding. Patch all holes and cracks with an appropriate patching compound, sand smooth and prime. Plaster, concrete block, concrete and other masonry surfaces must be cured. Remove all form release and curing agents. If the pH is higher than 8, prime with 166. Bare metal and raw wood must be primed. Galvanized surfaces shall have all oils removed prior to application of coating. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

hallman/lindsay PRIMER RECOMMENDATIONS

NEW WORK

Appropriate Builders Legacy Wall Prep primer, Smooth Hi-Build or Texture Hi-Build

Drywall: Smooth or textured finished as desired

Appropriate Foundations Specialty Primer

Masonry: Rough/Smooth, Concrete Block, Brick, Wood, Plaster, Metal: Ferrous (Steel), Non-ferrous (Galvanized)

REPAINT

Self priming (requires 2 coats) or 259 if specified, spot prime bare areas with appropriate Foundations Specialty Primer,

hallman/lindsay FINISH RECOMMENDATIONS

One or two coats 280

APPLICATION

Mix thoroughly before use. Apply by brush, roller, airless, HVLP or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Do not brush or roll excessively. Reducing material for spray application should not exceed 10%.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum ¾ GPM with .017" tip @ 2500 PSI
- ✓ Conventional: Binks #7 gun, 38 needle, 36 air nozzle, 38 fluid nozzle, 9.3 CFM @ 30 PSI
- ✓ HVLP: Twin-stage turbine, 5–8 PSI, .051 to .070 projector set
- ✓ Roller: ½" – ¾" nap synthetic cover
- ✓ Brush: 100% nylon or synthetic blend



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 ☎ www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.