



PRODUCT DATA SHEET

AQUA ALKYD

292

DESCRIPTION

Hallman/Lindsay's Aqua Alkyd is a premium durable interior/exterior waterborne alkyd enamel formulated with a bio-renewable medium oil alkyd latex. Aqua Alkyd sands easily and offers smooth application with outstanding flow and leveling of a high quality alkyd enamel but offers soap and water clean-up.

AQUA ALKYD may be used on properly primed or previously painted wood and metal trim, cabinets and doors. It may be used on applications ranging from residential and multi-family to commercial and institutional, along with light industrial facilities.

FEATURES

- ✓ Easy application with outstanding flow and leveling
- ✓ Low odor
- ✓ Zero VOC per EPA Method 24
- ✓ **NOTE:** Material VOC content at or below 5g/L. This is based on an interpretation of the SCAQMD Rule 314 exemption for "Zero VOC equivalent" coatings.
- ✓ Exceptional Enamel Finish
- ✓ Soap and Water clean up
- ✓ High-Hiding
- ✓ LEED v4 Certificate of Compliance for Emissions available upon request

PERFORMANCE DATA

- ✓ **Meets criteria set forth by the U.S. Green Building Council LEED-NC, version 2.2 and LEED-CI version 2.0.**

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Do not apply directly to wood species such as redwood and cedar which contain tannins or other water soluble materials. Must be primed with appropriate stain blocking primer.
- ✓ **Like conventional alkyds, Aqua Alkyd will yellow over time. Yellowing will be most noticeable when using off whites for interior applications in areas that do not receive sunlight.**
- ✓ Do not use on floors.
- ✓ Do not apply directly to zinc, galvanized or aluminum surfaces, must be primed before top coating.
- ✓ Do not apply to main body of exterior structures. Designed for use on doors trim and other small areas.
- ✓ Apply only if air, surface and material temperatures remain 50°F or above during application and dry time.

TECHNICAL DATA

- ✓ Color/Tinting:
White and tint bases
- ✓ Vehicle Type:
Alkyd Latex Hybrid
- ✓ Gloss: Satin
20-25 units @ 60°
- ✓ Percent Solids by Volume:
40% + 2
- ✓ Pigment by Weight:
32% + 2
- ✓ Vehicle Solids by Weight
23% + 2
- ✓ Recommended Spreading Rate:
Apply at 400 sq. ft./gal. to achieve
4.0 mils Wet Film Thickness
2.1 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Weight per Gallon:
11.00 lbs.
- ✓ Drying Time at 77°F 50% R.H.:
To touch: 4-6 hours
Recoat: Overnight
- ✓ Cleanup:
Water
- ✓ Thinning:
If needed thin sparingly with Water
- ✓ VOC: (EPA Method 24):
0 g/L 0 lbs./gal.

Products of Hallman/Lindsay Paints
Sun Prairie, WI 53590

9
Finishes
Painting (09900)

TECHNICAL SERVICES



FACTORY & MAIN OFFICES
Ph. 608/834-8844
Fax 608/837-1064
www.hallmanlindsay.com

SURFACE PREPARATION

Surfaces must be thoroughly dry, clean and free of dust, dirt, oil, grease, wax, chalk, rust or any other contaminants that may prevent proper adhesion and curing. Remove all loose or peeling paint. Glossy surfaces must be dulled by sanding. Pre-primed surfaces should be lightly sanded. Bare metal and wood must be primed. Galvanized surfaces shall have all oils removed and be properly primed prior to application of coating. Patch all holes and cracks with appropriate patching compound, sand smooth and prime. Primer must be thoroughly cured. Warning! If you scrape sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-lead or log on to www.epa.gov/lead

hallman/lindsay PRIMER RECOMMENDATIONS

NEW WORK

Wood containing Tannins or other	One coat 526
Water Soluble stain compounds	
Wood Interior:	One coat 231 or 526
Wood Exterior:	One coat 111 112 or 526
Rough Masonry/Concrete Block:	One coat 181 or 184
Smooth Masonry/Brick/Plaster:	One coat 166 or 231
Metal, Ferrous (Steel):	One coat 330 or 338
Metal, Non-Ferrous (Galvanized):	One coat 338

REPAINT WORK

Primer: Spot-prime all bare areas with appropriate **Foundations** Specialty Primer

hallman/lindsay FINISH RECOMMENDATIONS

One or two coats 292

APPLICATION

Stir thoroughly before and occasionally during use. Apply by brush, roller, airless, HVLP or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes to avoid lap marks. Surfaces should be dry prior to paint application.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum 3/4 GPM, .015” tip @ 2500 PSI
- ✓ Conventional: Binks #7 gun, 38 needle, 36 air nozzle, 38 fluid nozzle, 9.3 CFM@30 PSI
- ✓ HVLP: Twin-stage turbine, 5-8 PSI, .051 to .070 projector set
- ✓ Roller: 1/4” nap shed-resistant synthetic cover
- ✓ Brush: Natural china bristle or synthetic blend.



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.