



PRODUCT DATA SHEET

GOAL LINE

READY MIX ATHLETIC FIELD MARKING

306

DESCRIPTION

GOAL LINE READY MIX ATHLETIC FIELD MARKING is a pre mixed, 1/1 reduction, top-quality, latex field marking paint that is nontoxic, non-poisonous, non-irritating and harmless to grass or sod. When properly applied, it will form a solid, blur-proof line that is very durable and economical. May be used to mark tracks, tennis courts, football, baseball and other athletic fields.

FEATURES

- ✓ High-Hiding
- ✓ Non-Hazardous
- ✓ Zero VOC per EPA method 24
- ✓ Will Not Harm Grass or Sod
- ✓ Pre-mixed 1 to 1 Reduction

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL DATA

- ✓ Color/Tinting:
White. May be tinted with low VOC colorants. Also available in Yellow 306Y
- ✓ Vehicle Type:
Ethylene-Vinyl Acetate
- ✓ Gloss: Flat
- ✓ Percent Solids by Weight:
25% ± 2
- ✓ Percent Solids by Volume:
12% ± 2
- ✓ Pigment by Weight:
23% ± 2
- ✓ Vehicle Solids by Weight:
1.8% ± 2
- ✓ Recommended Spreading Rate:
250-300 sq.ft./gallon
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique etc.
- ✓ Weight per Gallon:
9.81 lbs.
- ✓ Drying Time at 77° F 50% R.H.:
2 hours
- ✓ Thinning/Cleanup:
Water
- ✓ VOC: (EPA Method 24)
0.0g/L 0.0 lbs./gal.
NOTE: Material VOC content at or below 5g/L. This is based on an interpretation of the SCAQMD Rule 314 exemption for "Zero VOC equivalent" coatings.

TECHNICAL SERVICES



FACTORY & MAIN OFFICES

Ph. 608/834-8844
Fax 608/837-1064
www.hallmanlindsay.com

Rev.3/16

SURFACE PREPARATION

Asphalt tracks should be clean and dry. Dirt or grass surfaces may be dew laden or slightly damp.

hallman/lindsay PRIMING RECOMMENDATIONS

Not required.

APPLICATION

Spray application is best for sharpest lines, produced by marking machine. Refer to machine manufacturer's instructions.

Roller or brush application is acceptable. Use synthetic brush or rollers.



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ① FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.