



PRODUCT DATA SHEET

SMOOTH HI-BUILD

PRO LO-SHEEN

362-1

DESCRIPTION

hallman/lindsay's **Builders Legacy** is our finest line of finishes designed for new drywall surfaces. All of our **Builders Legacy** products meet LEEDS criteria for new construction.

PRO SMOOTH HI-BUILD LO-SHEEN is a high-quality, high-build smooth finish. It has outstanding hide and is very washable. Designed for use in new construction in the home and multi-family markets, it can also be used in institutional, commercial and light industrial facilities.

FEATURES

- ✓ **Meets criteria set forth by the U.S. Green Building Council LEED-NC, version 2.2 and LEED-CI version 2.0.**
- ✓ Hi-Build Latex Formula
- ✓ Washable
- ✓ Attractive lo-sheen Finish
- ✓ Aids in Hiding Minor Defects
- ✓ One-Coat Coverage Over Most Surfaces

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL DATA

- ✓ Color/Tinting:
Pro White. May be tinted.
- ✓ Vehicle Type:
Ethylene-vinyl acetate
- ✓ Finish: Lo-sheen
3-5 units @ 60°
- ✓ Percent Solids:
Weight: 56% ± 2
Volume: 38% ± 2
- ✓ Recommended Spreading Rate:
Apply at 160 sq.ft./gal. to achieve
10. mils Wet Film Thickness
3.8 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Drying Time at 77°F 50% R.H.:
To touch: 1 hour
Recoat: Overnight
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
- ✓ Thinning/Cleanup:
Water
- ✓ VOC:
40 g/L 0.33 lbs./gal.

Products of Hallman/Lindsay Paints
Sun Prairie, WI 53590

9 Finishes
Painting (09900)

TECHNICAL SERVICES



FACTORY & MAIN OFFICES
Ph. 608/834-8844
Fax 608/837-1064
www.hallmanlindsay.com

SURFACE PREPARATION

Surfaces must be dry, clean and free of dust, dirt, grease, wax, oil, chalk, rust or any other contaminants that may prevent proper adhesion. All loose paint must be removed and glossy surfaces dulled by sanding. Plaster surfaces must be well cured and porous masonry surfaces should be filled with block filler. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Galvanized surfaces shall have all oils removed prior to application of coating. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

hallman/lindsay FINISH RECOMMENDATIONS

May be used as a primer under appropriate **hallman/lindsay** top coat.

OPTION

May also be used as a single-coat system.

APPLICATION

Mix thoroughly before use. Apply by airless spray for best results. May be applied by brush or roller; however, all properties related to hide and appearance may be affected. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Do not brush or roll excessively. Reducing material for spray application should not exceed 10%.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum 1 GPM with .021" tip @ 2900 PSI
- ✓ Conventional: Binks #7 gun, 38 needle, 36 air nozzle, 38 fluid nozzle, 9.3 CFM @ 30 PSI
- ✓ HVLP: Twin-stage turbine, 5 – 8 PSI, .051 to .070 projector set
- ✓ Roller: ½" – 1" nap synthetic cover
- ✓ Brush: 100% nylon or synthetic blend



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 ☎ www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.