



PRODUCT DATA SHEET

HI-BUILD PRO SURFACER

367

DESCRIPTION

hallman/lindsay's **Builders Legacy** is our finest line of finishes designed for new drywall surfaces. All of our **Builders Legacy** products meet LEEDS criteria for new construction.

HI-BUILD PRO SURFACER is a quality, high build latex primer/surfacer formulated for use on interior drywall, gypsum board, cured plaster and under decorative texture and finishes.

PRO-PRIMER SURFACER will provide a uniform surface over varying substrate surfaces such as the face paper, joints and nail heads on sheetrock. Its high build formulation fills rough and uneven drywall to a uniform surface. It will minimize minor surface imperfections, sanding nicks, paper fuzz and mud pinholes.

Also available as 367SP and 367LV

FEATURES

- ✓ **Meets criteria set forth by the U.S. Green Building Council LEED-NC, version 2.2 and LEED-CI version 2.0.**
- ✓ Quick Dry
- ✓ Fills And Seals In One Application
- ✓ Ensures A Uniform Sheen
- ✓ Can Be Tinted With Up To 2oz. universal colorant per gallon
- ✓ Ideal For Use Under Decorative
- ✓ Texture Finishes
- ✓ Low Odor
- ✓ Zero VOC per EPA Method 24
- ✓ LEED v4 Certificate of Compliance for Emissions available upon request

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Must be topcoated.
- ✓ Joint compound must be completely dry.
- ✓ Not intended for use with Epoxy topcoats.
- ✓ When top coating with enamels apply 2 coats for full sheen development

TECHNICAL SERVICES

TECHNICAL DATA

- ✓ Color/Tinting:
White. May be tinted.
- ✓ Vehicle Type:
Ethylene Vinyl Acetate
- ✓ Finish: Flat
0-4 units @ 60°
- ✓ Percent Solids by Weight:
58% ± 2
- ✓ Percent Solids by Volume:
37% ± 2
- ✓ Pigment by Weight:
53% ± 2
- ✓ Vehicle Solids by Weight
5% ± 2
- ✓ Recommended Spreading Rate:
Apply at 160 sq.ft./gal to achieve
10 mils Wet Film Thickness
2.5 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Weight per Gallon:
10.63 lbs.
- ✓ Drying Time at 770 F 50% R.H.:
To touch: 1 hour
Recoat: Overnight
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
- ✓ Cleanup:
Water
- ✓ VOC (EPA Method 24):
0 g/L 0 lbs./gal

NOTE: Material VOC content at or below 5g/L. This is based on an interpretation of the SCAQMD Rule 314 exemption for "Zero VOC equivalent" coatings.

Products of Hallman/Lindsay Paints
Sun Prairie, WI 53590

9 Finishes
Painting (09900)



FACTORY & MAIN OFFICES
Ph. 608/834-8844
Fax 608/837-1064
www.hallmanlindsay.com

SURFACE PREPARATION

All joint compound on sheetrock joints and nailheads must be completely dry and sanded smooth. Any larger cracks, dings, holes or other damaged areas should be filled with the appropriate patching materials. Bleeding stains such as watermarks, ink, pencil etc. should be sealed with 526 StainGuard. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

hallman/lindsay FINISH RECOMMENDATIONS

Latex May be used as a primer under appropriate **hallman/lindsay** top coat.

Alkyd: **hallman/lindsay** 241, 242, 276, 290, or 311

Epoxy: Not recommended

APPLICATION

Apply by airless spray for best results. May be applied by brush or roller; however, all properties related to hide and appearance may be affected. Surfaces should be clean and dry prior to paint application.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum 1 GPM, .021" tip @ 2900 PSI
- ✓ Conventional: Binks 2001 gun, 568 needle, 201 air nozzle, 68SS fluid nozzle, 5.8 CFM @ 50 PSI
- ✓ HVLP: 3 to 4 stage turbine, 6 - 8 PSI, .051-.070 projector set
- ✓ Roller: ½" - 1" nap synthetic roller cover
- ✓ Brush: 100% nylon or synthetic blend



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ① FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.