



PRODUCT DATA SHEET

DRYWALL PRIMER

368

DESCRIPTION

hallman/lindsay's **Builders Legacy** is our line of finishes designed for new drywall surfaces. All of our **Builders Legacy** products meet LEEDS criteria for new construction.

Builder's Legacy DRYWALL PRIMER is a production latex wall primer that is designed to be applied to new interior drywall and gypsum board walls and ceilings. It provides a uniform surface for even and consistent topcoat application. It is a primer that has low odor and low VOC. Not intended for use as a finish coat or as a primer under wall coverings.

It is designed for use in the new construction, multi- family housing and commercial institutional industries.

FEATURES

- ✓ **Meets criteria set forth by the U.S. Green Building Council LEED-NC, version 2.2 and LEED-CI version 2.0.**
- ✓ Formulated for New Drywall and Gypsum Board
- ✓ Zero VOC per EPA Method 24
- ✓ **NOTE:** Material VOC content at or below 5g/L. This is based on an interpretation of the SCAQMD Rule 314 exemption for "Zero VOC equivalent" coatings.
- ✓ Low-Odor
- ✓ Soap and Water Cleanup
- ✓ Professional Application

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL DATA

- ✓ Color/Tinting:
Off White.
- ✓ Vehicle Type:
Ethylene-Vinyl Acetate
- ✓ Gloss: Flat
1-2 units @ 60°
- ✓ Percent Solids:
Weight: 59% ± 2
Volume: 38% ± 2
- ✓ Recommended Spreading Rate:
Apply at 200 sq.ft./gal. to achieve
6.0 mils Wet Film Thickness
2.3 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Drying Time at 77° F 50% R.H.:
To touch: 1 hour
Recoat: 2 hours
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
- ✓ Thinning/Cleanup:
Water
- ✓ VOC (EPA Method 24):
0 g/L 0 lbs./gal

Products of Hallman/Lindsay Paints
Sun Prairie, WI 53590

9 Finishes
Painting (09900)

TECHNICAL SERVICES



FACTORY & MAIN OFFICES
Ph. 608/834-8844
Fax 608/837-1064
www.hallmanlindsay.com

SURFACE PREPARATION

Surfaces must be dry, clean and free of dirt, oil, chalk, efflorescence or any other contaminants that may prevent proper adhesion. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

hallman/lindsay FINISH RECOMMENDATIONS

Designed for use under appropriate **hallman/lindsay** flat topcoats.

APPLICATION

Mix thoroughly before use. Apply by airless spray for best results. May be applied by brush or roller; however, all properties related to hide and appearance may be affected. Do not brush or roll excessively. Reducing material for spray application should not exceed 10%.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum ¾ GPM with .017" tip @ 2700 PSI
- ✓ Conventional: Binks #7 gun, 38 needle, 36 air nozzle, 38 fluid nozzle, 9.3 CFM @ 30 PSI
- ✓ HVLP: Twin-stage turbine, 5 – 8 PSI, .051 to .070 projector set
- ✓ Roller: 1/2" - 1" nap synthetic cover
- ✓ Brush: 100% nylon or synthetic blend



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ① FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.