



# PRODUCT DATA SHEET

## CLASSIC SPATTER KOTE

### 369

#### DESCRIPTION

hallman/lindsay's **Builders Legacy** is our finest line of finishes designed for new drywall surfaces. All of our **Builders Legacy** products meet LEEDS criteria for new construction

CLASSIC SPATTER KOTE wall surfacer is designed to be applied to new interior drywall and gypsum board walls and ceilings. It provides a multidimensional surface and requires a topcoat application. It may be applied to provide a spatter or orange peel surface. It provides a hard surface for a variety of latex or oil topcoats. It features high solids, low odor and low VOC, formulated for quick recoat times, depending on the film build. It should be topcoated with desired hallman/lindsay primer or finish. Not intended for use as a finish coat or as a primer under wall coverings.

#### FEATURES

- ✓ **Meets criteria set forth by the U.S. Green Building Council LEED-NC, version 2.2 and LEED-CI version 2.0.**
- ✓ Formulated for New Drywall and Gypsum Board
- ✓ High Solids
- ✓ Low-Odor
- ✓ High Film Build
- ✓ Excellent Sag Resistance
- ✓ Soap and Water Cleanup
- ✓ Accepts Latex and Alkyd Topcoats
- ✓ Tougher than Bag Mix
- ✓ Zero VOC per EPA Method 24
- ✓ **NOTE:** Material VOC content at or below 5g/L. This is based on an interpretation of the SCAQMD Rule 314 exemption for "Zero VOC equivalent" coatings.

#### PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.
- ✓ Intended For Professional Application
- ✓ Not Intended for Use as a Finish Coat or as a Primer under Wallcovering.

#### TECHNICAL DATA

- ✓ Color/Tinting:  
White. Do not tint
- ✓ Vehicle Type:  
Ethylene Vinyl Acetate
- ✓ Finish: Flat  
2-4 units @ 60°
- ✓ Percent Solids:  
Weight: 64% + 2  
Volume: 40% + 2
- ✓ Recommended Spreading Rates:  
Apply up to 150 sq.ft./gal. For Spatter, Orange Peel  
Max.film build:50 mils Wet Film Thickness  
20 mils Dry Film Thickness  
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Drying Time at 770 F 50% R.H.:  
To touch: 1 to 24 hours  
Recoat: 2-24 hours  
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
- ✓ Cleanup:  
Water
- ✓ VOC (EPA Method 24):  
0 g/L      0 lbs./gal

Products of Hallman/Lindsay Paints  
Sun Prairie, WI 53590

9 Finishes  
Painting (09900)



**FACTORY & MAIN OFFICES**  
Ph. 608/834-8844  
Fax 608/837-1064  
[www.hallmanlindsay.com](http://www.hallmanlindsay.com)

## **SURFACE PREPARATION**

Surfaces must be dry, clean, free of dirt, oil, chalk, or any other contaminants that may prevent proper adhesion. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

## **hallman/lindsay FINISH RECOMMENDATIONS**

May be top coated with any appropriate **hallman/lindsay** primer or finish coat. For best results two coats recommended.

## **APPLICATION**

Designed for use with air assisted airless spray or hopper gun. May also be applied by airless spray. Apply only if air, surface and paint temperature are above 50°F, and will remain so until film is dry.

## **EQUIPMENT REQUIREMENTS**

- ✓ Air assisted airless: 7 or 10 to 1 pump, Binks #7D gun, H series convertible nozzles, 16-20 cfm @ 150 PSI.
- ✓ Hopper Gun
- ✓ Airless: Spray Tech 2510 with 630 Zip-Tip.
- ✓ Benron Texture Pump



### **FACTORY & MAIN OFFICES**

1717 N. Bristol Street ☒ Sun Prairie, WI 53590  
☎ (608) 834-8844 ① FAX (608) 837-1064 🌐 [www.hallmanlindsay.com](http://www.hallmanlindsay.com)

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.