



PRODUCT DATA SHEET

PREMIUM SPATTER KOTE

370

DESCRIPTION

hallman/lindsay's **Builders Legacy** is our finest line of finishes designed for new drywall surfaces. All of our **Builders Legacy** products meet LEEDS criteria for new construction.

PREMIUM SPATTER KOTE wall surfacer is designed to be applied to new interior drywall and gypsum board walls and ceilings. It provides a multidimensional surface and requires a topcoat application. It may be applied to provide a spatter, knockdown or skip trowel surface. It provides a hard, tough base for a variety of latex or oil topcoats. It features high solids, low odor and low VOC, Formulated for quick recoat times, depending on the film build. It should be topcoated with desired **hallman/Lindsay** primer or finish. Not intended for use as a finish coat or as a primer under wallcoverings.

FEATURES

- ✓ **Meets criteria set forth by the U.S. Green Building Council LEED-NC, version 2.2 and LEED-CI version 2.0.**
- ✓ Formulated for New Drywall and Gypsum Board
- ✓ High Solids
- ✓ Low-Odor
- ✓ High Film Build
- ✓ Excellent Sag Resistance
- ✓ Soap and Water Cleanup
- ✓ Accepts Latex and Alkyd Topcoats
- ✓ Tougher than Bag Mix

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.
- ✓ Intended For Professional Application
- ✓ Not Intended for Use as a Finish Coat or as a Primer under Wallcovering.

TECHNICAL SERVICES



FACTORY & MAIN OFFICES

Ph. 608/834-8844

Fax 608/837-1064

www.hallmanlindsay.com

TECHNICAL DATA

- ✓ Color/Tinting:
White. Do not tint
- ✓ Vehicle Type:
Ethylene Vinyl Acetate
- ✓ Finish: Flat
2-4 units @ 60°
- ✓ Percent Solids by Weight:
64% + 2
- ✓ Percent Solids by Volume:
41% + 2
- ✓ Pigment by Weight:
60% + 2
- ✓ Vehicle Solids by Weight:
4% + 2
- ✓ Recommended Spreading Rates:
Apply up to 150 sq.ft./gal. For Spatter, Orange Peel or Knockdown
Max.film build:100 mils Wet Film Thickness
42 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Weight per Gallon:
13.45 lbs.
- ✓ Drying Time at 770 F 50% R.H.:
To touch: 1 to 24 hours
Recoat: 2-24 hours
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
- ✓ Cleanup:
Water
- ✓ VOC (EPA Method 24):
0 g/L 0 lbs./gal

NOTE: Material VOC content at or below 5g/L. This is based on an interpretation of the SCAQMD Rule 314 exemption for "Zero VOC equivalent" coatings.

SURFACE PREPARATION

Surfaces must be dry, clean, free of dirt, oil, chalk, or any other contaminants that may prevent proper adhesion. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

hallman/lindsay FINISH RECOMMENDATIONS

May be used as a primer under appropriate **hallman/lindsay** top coat.

APPLICATION

Apply without stirring to produce maximum film build for knockdown or skip trowel effect. For spatter or crows foot effect stir slightly before use. Designed for use with air assisted airless spray or hopper gun. May also be applied by airless spray. Reducing material for spray application should not exceed 10% for light texture applications. Apply only if air, surface and paint temperature are above 50°F, and will remain so until film is dry.

EQUIPMENT REQUIREMENTS

- ✓ Air assisted airless: 7 or 10 to 1 pump, Binks #7D gun, H series convertible nozzles, 16-20 cfm @ 150 PSI.
- ✓ Hopper Gun
- ✓ Airless: Spray Tech 2510 with 630 Zip-Tip.
- ✓ Wagner Texture Pump



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 ☎ www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.