



PRODUCT DATA SHEET

PREMIUM SKIM KOTE LEVEL 5 SURFACER

371

DESCRIPTION

hallman/lindsay's **Builders Legacy** is our finest line of finishes designed for new drywall surfaces. All of our **Builders Legacy** products meet LEEDS criteria for new construction.

PREMIUM SKIM KOTE LEVEL 5 SURFACER is designed to be applied to new interior drywall and gypsum board walls and ceilings. It provides a finish similar to a level 5 finish, normally achieved by skim coating the surface with drywall compound or plaster. It provides an excellent primed surface or can be left unpainted on ceilings as a finish coat. It will accept a variety of topcoats.

FEATURES

- ✓ **Meets criteria set forth by the U.S. Green Building Council LEED-NC, version 2.2 and LEED-CI version 2.0.**
- ✓ Formulated for New Drywall and Gypsum Board
- ✓ High Solids
- ✓ High Film Build
- ✓ Excellent Sag Resistance
- ✓ Fast-Dry
- ✓ Zero VOC per EPA Method 24
- ✓ Low-Odor
- ✓ Soap and Water Cleanup
- ✓ Accepts Latex and Alkyd Topcoats
- ✓ Professional Application
- ✓ LEED v4 Certificate of Compliance for Emissions available upon request

PERFORMANCE DATA

- ✓ Performance alternate for Federal Paint Specification TT-P-25 F

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL SERVICES



FACTORY & MAIN OFFICES
 Ph. 608/834-8844
 Fax 608/837-1064
www.hallmanlindsay.com

TECHNICAL DATA

- ✓ Color/Tinting:
White. Do not tint
- ✓ Vehicle Type:
Ethylene Vinyl Acetate
- ✓ Finish: Flat
2-4 units @ 60°
- ✓ Percent Solids by Weight:
59% ± 2
- ✓ Percent Solids by Volume:
38% ± 2
- ✓ Pigment by Weight:
49% ± 2
- ✓ Vehicle Solids by Weight
9% ± 2
- ✓ Recommended Spreading Rate:
Up to 150 sq.ft. /gal.
15-20 mils Wet Film Thickness
6.0-8.0 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Weight per Gallon:
12.45 lbs.
- ✓ Drying Time at 770 F 50% R.H.:
To touch: 1 to 24 hours
Recoat: 2-24hours
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
- ✓ Cleanup:
Water
- ✓ VOC (EPA Method 24):
0 g/L 0 lbs./gal.

NOTE: Material VOC content at or below 5g/L. This is based on an interpretation of the SCAQMD Rule 314 exemption for "Zero VOC equivalent" coatings.

SURFACE PREPARATION

Surfaces must be dry, clean and free of dirt, oil, chalk, or any other contaminants that may prevent proper adhesion. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to avoid photographing. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

hallman/lindsay FINISH RECOMMENDATIONS

Maybe topcoated with any APPROPRIATE **hallman/lindsay** finish.

APPLICATION

Airless spray application only. Using the equipment listed below as a minimum apply material 12-18 "from surface with a 50% overlap to insure keeping a "wet edge". Apply from left to right for initial application with subsequent cross application to insure proper film thickness. Minimum 20 mils wet for total film application will achieve desired effect.

EQUIPMENT REQUIREMENTS

✓ Airless: 1 GPM airless with 3/8" hose and .025-.031 tip, 2500-3000psi, 30 mesh filter



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ① FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.