



PRODUCT DATA SHEET

FAST DRY AQUA ZONE

100% ACRYLIC TRAFFIC MARKING

473

DESCRIPTION

AQUA ZONE 100% ACRYLIC TRAFFIC MARKING is a high hiding marking paint formulated for use on asphalt and concrete surfaces. Use when a fast dry to no pick up time is required. For use on highways, in parking lots, shopping centers, airfields, schools, cities and towns.

The fast dry formula works well under poor drying conditions such as high humidity and low air flow.

Also available in yellow, FAST DRY AQUA ZONE 473Y.

FEATURES

- ✓ 100% Fastrack Acrylic™
- ✓ Fast Dry-to-No-Pickup Times
- ✓ High Solids Formula
- ✓ Asphalt Surface will Not Bleed Through
- ✓ Excellent Abrasion Resistance
- ✓ Exceptional Glass Bead Retention
- ✓ Non Flammable
- ✓ Low VOC
- ✓ Soap and water clean up

PERFORMANCE DATA

Performance alternate for Federal Paint Specification TT-P-1952E Type I & II

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL SERVICES



FACTORY & MAIN OFFICES

Ph. 608/834-8844

Fax 608/837-1064

www.hallmanlindsay.com

TECHNICAL DATA

- ✓ Color: White
- ✓ Vehicle Type: 100% Acrylic
- ✓ Gloss: Flat
0-4 units @ 60°
- ✓ Percent Solids:
Weight: 74% ± 2
Volume: 56% ± 2
- ✓ Recommended Spreading Rate:
15.0 mils Wet Film Thickness
8.4 mils Dry Film Thickness
A 4" continuous line applied at 15 mils wet will cover approximately 320 feet.
Weight per Gallon:
14.14 lbs.
- ✓ Drying Time @ 15 mils wet @ 77° F with 50% humidity: Less than 5 minutes, No pick up – 1-2 minutes when paint heated to between 90 and 110 degrees F.
- ✓ Thinning/Cleanup:
Water
- ✓ VOC:
85 g/L 0.71 lbs. /gal.

SURFACE PREPARATION

Surfaces must not contain puddled water.

APPLICATION

Mix thoroughly before use. Apply by conventional or airless spray.

EQUIPMENT REQUIREMENTS:

- ✓ Airless: .217-.230 tip size
- ✓ Conventional: Internal mix .028 fluid nozzle and air cap assembly



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.