



PRODUCT DATA SHEET

AQUA ZONE

100% ACRYLIC TRAFFIC MARKING

474

DESCRIPTION

AQUA ZONE 100% ACRYLIC TRAFFIC MARKING is a high hiding marking paint formulated for use on asphalt and concrete surfaces. Use when a fast dry to no pick up time is required. For use in parking lots, shopping centers, airfields, schools, cities and towns.

The fast dry formula works well under poor drying conditions such as high humidity and low air flow.

Also available in yellow, AQUA ZONE 474Y.

FEATURES

- ✓ 100% Fastrack Acrylic™
- ✓ Fast Dry-to-No-Pickup Times
- ✓ Asphalt Surface will Not Bleed Through
- ✓ Excellent Abrasion Resistance and Durability
- ✓ Non Flammable
- ✓ Low VOC
- ✓ Soap and water clean up

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL DATA

- ✓ Color: White
- ✓ Vehicle Type: 100% Acrylic
- ✓ Gloss: Flat
0-4 units @ 60°
- ✓ Percent Solids by Weight:
65% ± 2
- ✓ Percent Solids by Volume:
46% ± 2
- ✓ Pigment by Weight:
54% ± 2
- ✓ Vehicle Solids by Weight:
10% ± 2
- ✓ Recommended Spreading Rate:
6.0 mils Wet Film Thickness
3.0 mils Dry Film Thickness
A 4" continuous line applied at 6.0 mils wet will cover approximately 270 feet.
When calculating working coverage, allow for application losses, texture and porosity of surface, application techniques etc.
- ✓ Weight per Gallon:
12.77 lbs.
- ✓ Drying Time @ 6 mils wet @ 77° F with 50% humidity: Less than 5 minutes.
- ✓ Thinning/Cleanup:
Water
- ✓ VOC:
84 g/L 0.70 lbs. /gal.

Products of Hallman/Lindsay Paints
Sun Prairie, WI 53590

9
Finishes
Painting (09900)

TECHNICAL SERVICES



FACTORY & MAIN OFFICES
Ph. 608/834-8844
Fax 608/837-1064
www.hallmanlindsay.com

Rev. 2/16

SURFACE PREPARATION

Surfaces must not contain puddled water.

APPLICATION

Mix thoroughly before use. Apply by airless spray.

EQUIPMENT REQUIREMENTS:

- ✓ Airless: .217-.230 tip size



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 ☎ www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.