



PRODUCT DATA SHEET

AQUA PRECAT

WATERBORNE ACRYLIC PRECAT EPOXY

514

DESCRIPTION

hallman/lindsay's *ProSeries* is our full line of finishes designed for the professional contractor.

AQUA PRECAT WATERBORNE ACRYLIC PRECAT EPOXY is a water-based, pre-catalyzed, single package acrylic epoxy for use on interior surfaces. It offers a durable finish resistant to dirt stains and the cleaning solutions needed to remove them.

It is ideally suited for walls, ceilings and trim in areas that require frequent maintenance such as those that are found in hospitals, schools, institutions, offices, warehousing and manufacturing, universities and public buildings. May be used on a variety of surfaces such as brick, masonry, metal, drywall and wood.

FEATURES

- ✓ **Meets criteria set forth by the U.S. Green Building Council LEED-NC, version 2.2 and LEED-CI version 2.0.**
- ✓ Attractive Scrubbable Eggshell Enamel Finish
- ✓ Low-Odor, Water-Based Formula
- ✓ Low-VOC
- ✓ Use on a Variety of Substrates
- ✓ Easy Soap and Water Cleanup
- ✓

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.
- ✓ For interior use only.

TECHNICAL DATA

- ✓ Color/Tinting:
Pro White. May be tinted, up to 4 oz. per gallon, with most universal colorants
 - ✓ Vehicle Type:
Epoxy-Acrylic copolymer
 - ✓ Finish: Eggshell
11-14 units @ 60° 16-20 @ 85°
 - ✓ Percent Solids by Weight:
Weight: 50% ± 2
Volume: 34% ± 2
 - ✓ Recommended Spreading Rate:
Apply at 350 sq./gal. to achieve
4.0 mils Wet Film Thickness
1.5 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
 - ✓ Drying Time at 77°F 50% R.H.:
To touch: 4 hours
Recoat: Overnight
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
 - ✓ VOC:
44 g/L 0.37 lbs./gal.
- Satisfies USDA requirements for incidental food contact.

TECHNICAL SERVICES



FACTORY & MAIN OFFICES
Ph. 608/834-8844
Fax 608/837-1064
www.hallmanlindsay.com

Rev. 3/18

Products of Hallman/Lindsay Paints
Sun Prairie, WI 53590

9
Finishes
Painting (09900)

SURFACE PREPARATION

Surfaces must be dry, clean and free of dirt, oil, grease, wax, dust, chalk, rust or any other contaminants that may prevent proper adhesion. Remove all loose or peeling paint. Glossy surfaces must be dulled by sanding. All unpainted surfaces must be primed. Patch all holes and cracks with appropriate patching compound and sand smooth. Galvanized surfaces shall have all oils removed prior to application of coating. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

hallman/lindsay FINISH RECOMMENDATIONS

NEW WORK

Wood:	One coat 231
Rough Masonry/Concrete Block:	One coat 179 or 181
Smooth Masonry/Brick/Plaster:	One coat 166 or 231
Metal, Ferrous (Steel):	One coat 330 or 338
Metal, Non-Ferrous (Galvanized):	One coat 338
Drywall:	One coat 220

PREVIOUSLY PAINTED SURFACES

May be applied over existing coatings only after sample applications have been made to check the sensitivity of the existing coating. Surfaces must be primed and properly prepared if sensitivity or lifting occurs.

hallman/lindsay FINISH RECOMMENDATIONS

One to two coats 514

APPLICATION

Apply by brush, roller, airless, HVLP or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Surfaces should be dry prior to paint application.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum ¾ GPM with .017" tip @ 2500 PSI
- ✓ Conventional: Binks #7 gun, 38 needle, 36 air nozzle, 38 fluid nozzle, 9.3 CFM @ 30 PSI
- ✓ HVLP: Twin-stage turbine, 5 – 8 PSI, .051 to .070 projector set
- ✓ Roller: 3/8" – ¾" nap shed-resistant cover or lambswool cover
- ✓ Brush: 100% Nylon or synthetic blend



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.