



PRODUCT DATA SHEET

JET DRY

WATERBORNE ACRYLIC PRIMER/SURFACER

600

DESCRIPTION

hallman/lindsay's *ProSeries* is our full line of finishes designed for the professional contractor.

JET DRY WATER-BORNE ACRYLIC PRIMER/ SURFACER is a premium, quick-dry waterborne primer/sealer designed for professional application during construction. Its high-solids, acrylic formula provides a uniform, even finish for interior surfaces. It is ideal for use as a primer, sealer and filler for wood surfaces. Use on wood surfaces such as trim, MDF board, molding, furniture, cabinets, doors and shelving.

JET DRY'S quick-dry formula makes it ideally suited for spray application.

FEATURES

- ✓ Uniform Finish
- ✓ Fast Dry and Recoat
- ✓ Low-Odor
- ✓ Low-VOC
- ✓ Soap and Water Clean-up
- ✓ Enamel Holdout
- ✓ Fills Minor Imperfections

PERFORMANCE DATA

- ✓ Performance alternate for Federal Paint Specification TT-P-25 F

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL DATA

- ✓ Color/Tinting:
White. May be tinted, up to 2 oz. per gallon, with most universal colorants.
- ✓ Vehicle Type:
Acrylic Copolymer
- ✓ Gloss: Flat
0-5 units @ 60°
- ✓ Percent Solids by Weight:
73% ± 2
- ✓ Percent Solids by Volume:
54% ± 2
- ✓ Pigment by Weight:
53% ± 2
- ✓ Vehicle Solids by Weight
19% ± 2
- ✓ Recommended Spreading Rate:
Apply at 400 sq.ft./gal. to achieve
4.0 mils Wet Film Thickness
2.2 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Weight per Gallon:
14.2 lbs.
- ✓ Drying Time at 77°F 50% R.H.:
To touch: 30 minutes
Recoat: 1 hour
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
- ✓ Thinning/Cleanup:
Water
- ✓ VOC:
31 g/L 0.26 lbs./gal.

TECHNICAL SERVICES



FACTORY & MAIN OFFICES
 Ph. 608/834-8844
 Fax 608/837-1064
www.hallmanlindsay.com

Rev. 6/15

SURFACE PREPARATION

Surfaces must be dry, clean and free of dirt, oil, grease, wax, dust or any other contaminants that may prevent proper adhesion. Remove all loose or peeling paint. Glossy surfaces must be dulled by sanding. Patch all holes and cracks with appropriate patching compound and sand smooth. Remove all dust with a vacuum or damp, white cloth. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

hallman/lindsay FINISH RECOMMENDATIONS

Latex: 315, 316, 317, 318, or 620
Alkyd: 276, 290 or 311

APPLICATION

Mix thoroughly before use. Designed to be professionally applied by airless, HVLP or conventional spray. May be brushed on small areas. Reducing material for spray application should not exceed 10%.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum ¾ GPM with .017" tip @ 2500 PSI
- ✓ Conventional: Binks #7 gun, 38 needle, 36 air nozzle, 38 fluid nozzle, 9.3 CFM @ 30 PSI
- ✓ HVLP: Twin-stage turbine, 5 – 8 PSI, .051 to .070 projector set
- ✓ Roller: Not recommended
- ✓ Brush: 100% nylon or synthetic blend



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 ☎ www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.