



PRODUCT DATA SHEET

WATERBORNE URETHANE

V365

DESCRIPTION

hallman/lindsay's **Wood Shades** are our finest interior wood stains and clear finishes.

WATERBORNE URETHANE FLOOR FINISH is a premium, self-crosslinking oil modified urethane varnish. Designed for the contractor and do-it yourself finisher for use in heavy traffic residential and commercial areas, sports floors, multi-purpose gyms and studios where a tough abrasion resistant coating is required.

FEATURES

- ✓ Self-Crosslinking Oxidative Cure
- ✓ Clear, Natural Amber Finish
- ✓ Attractive Satin Sheen
- ✓ Excellent Chemical and Stain Resistance
- ✓ Excellent Flow and Leveling
- ✓ Fast Dry
- ✓ Multiple Coats can be applied in One Day
- ✓ Low Odor
- ✓ Low VOC
- ✓ Non Flammable
- ✓ Soap and Water Clean-up

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets
- ✓ Allow final coat to dry 48 hours before use.
- ✓ Allow 7 days to reach full cure
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL DATA

- ✓ Color:
Natural Amber Clear Finish.
- ✓ Vehicle Type:
Oil Modified Urethane Dispersion
- ✓ Finish: Satin
25-30 units @ 60°
- ✓ Percent Solids by Weight:
33% ± 2
- ✓ Percent Solids by Volume:
29% ± 2
- ✓ Pigment by Weight:
3% ± 2
- ✓ Vehicle Solids by Weight
30% ± 2
- ✓ Recommended Spreading Rate:
Apply at 400-535 sq.ft./gal. to achieve
3.0-4.0 mils Wet Film Thickness
1.0-1.2 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Weight per Gallon:
8.6 lbs.
- ✓ Drying Time at 77°F 50% R.H.:
To touch: 1 hour
Recoat: 3 hours
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
- ✓ Cleanup:
Water
- ✓ VOC:
177 g/L 1.47 lbs./gal.

Products of Hallman/Lindsay Paints
Sun Prairie, WI 53590

9 Finishes
Painting (09900)

TECHNICAL SERVICES



FACTORY & MAIN OFFICES
Ph. 608/834-8844
Fax 608/837-1064
www.hallmanlindsay.com

SURFACE PREPARATION

Surfaces must be dry, clean and free of dust, dirt, grease, wax, oil, chalk, rust or any other contaminants that may prevent proper adhesion. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

hallman/lindsay SYSTEM RECOMMENDATIONS

NEW WORK:

Wood: Seal or Stain and Seal wood using 346.

REFINISH WORK:

Wood: Previously stained, painted or varnished surfaces should be thoroughly sanded and the dust removed before applying finish.

hallman/lindsay FINISH RECOMMENDATIONS

Apply minimum of 3 coats V365

APPLICATION

Stir thoroughly before use. Shaking will cause air bubbles to form in finish. Apply by swivel head floor roller with flocked foam roller, flocked foam pad or China Bristle brush. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Surfaces should be dry prior to application. Sanding with a 120 grit screen is recommended prior to application of finish to minimize grain raising. Sanding between finish coats is not necessary unless more than 48 hours have passed since the previous coat has been applied. Remove any sanding dust with a tack rag before applying next coat.

EQUIPMENT REQUIREMENTS

- ✓ Swivel head floor roller, with flocked foam cover
- ✓ Flocked foam pad
- ✓ 100% China Bristle brush



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.