

SURFACE PREPARATION

Surfaces must be clean, dry and free of dirt, oil, excessive chalk, or any other contaminants that may prevent proper adhesion. New plaster surfaces should be allowed to cure for at least 48 hours before applying PLASTER KOTE. To insure proper adhesion, plaster surfaces need to be inspected for dust or powder that may be present on the surface upon drying. If present, walls should be washed with a solution consisting of 1-pint household vinegar to 1-gallon of water. Repeat until surface is free of powder. Rinse with clear water and allow to dry. Contact your sales representative or contact the closest **hallman/lindsay** store for specific recommendations. **WARNING** : Removing old paint by sanding, scraping or other means may generate dust which may contain lead. Exposure to lead dust may cause adverse health effects, especially in children or pregnant women. Controlling exposure to hazardous substances requires using proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For additional information, contact USEPA/Lead Information Hotline at 1-800-LEAD-FYI.

hallman/lindsay FINISH RECOMMENDATIONS

Interior: Two Coats recommended for best results.

APPLICATION

Mix thoroughly before use. Apply by brush, roller or airless or conventional spray. If sprayed, product should be back-rolled or brushed to properly work into surface. Apply when the ambient, surface, and material temperatures 50° F or higher. Thinning is not recommended.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum 3/4 GPM with .019" tip @ 3000 PSI
- ✓ Conventional: Binks #7 gun, 38 needle, 36 air nozzle, 38 fluid nozzle 9.3 CFM @ 30PSI
- ✓ HVLP: Twin Stage Turbine, 5-8 PSI, .051 to .070 projector set
- ✓ Roller: ½" - 1½" nap synthetic cover, depending on surface
- ✓ Brush: Quality nylon /polyester brush



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.