

GRIPCRETE

BLOCK FILLER

184

PREMIUM SERIES
INTERIOR/EXTERIOR
FLAT
184
BLOCK FILLER

GRIPCRETE BLOCK FILLER is a general-purpose interior block filler designed to fill and smooth interior masonry surfaces. When applied properly, it will produce a paintable surface with reduced pin-holes to improve application and performance of subsequent finishes. The zero-VOC, LEED V4 compliant formulation meets the strictest air quality standards.

GRIPCRETE BLOCK FILLER is formulated for professional spray application to bare, unpainted masonry surfaces. The filing and sealing qualities makes it ideal for preparing masonry surfaces in commercial, institutional, and light industrial construction. Can be finished with professional latex finishes and waterborne pre-catalyzed epoxies.

COMPLIANCE & CERTIFICATION

Gloss Level	1
VOC Content	2.6 g/L 0.02 lb./Gal
LEED v4 Credit Eligible	YES

RECOMMENDED USAGE

- For Interior and Exterior Use
- Bare Masonry Surfaces

PERFORMANCE & FEATURES

- Excellent Fill & Sealing Properties
- High-Hiding Formula
- LEED v4 Credit Eligible

BENEFITS

Labor and Material Savings: Improved filling and sealing properties fills pores with fewer pin-holes reducing the amount of time and topcoat required to finish surfaces

Environmentally Responsible Coating: Low-odor, zero-VOC formula minimizes impact on other trades during application while meeting the strictest air quality standards.

PRODUCT SPECIFICATIONS

Vehicle Type: Ethylene-Vinyl Acetate

Color Tinting: White. May be tinted, up to 2 oz. per gallon, with low VOC colorants.

Gloss: Flat

0-5 units @ 60°

Solid Content: Weight: 69% ± 2

Volume: 48% ± 2

Drying Time: (75° F. & 50% R.H.)

To touch: 1 Hour

To recoat: Overnight

Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc. are present. Allow product to dry thoroughly before top coating

Theoretical Coverage:

Apply at 80-100 sq. ft./gal. to achieve

16-20 mils Wet Film Thickness

8.5-10.5 mils Dry Film Thickness

When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.

PRECAUTIONS/LIMITATIONS

- Please refer to Safety Data Sheets.
- For interior use only.
- Not to be used in areas subjected to severe moisture or with the intent as a waterproofer or below grade.
- Apply only if air, surface and material temperatures remain 50° F or above during application and drying.
- May be used on exterior surfaces but must be top coated within 30 days.



GRIPCRETE

BLOCK FILLER

184

PREMIUM SERIES
INTERIOR/EXTERIOR
FLAT
184
BLOCK FILLER

SURFACE PREPARATION

Surfaces must be dry, clean and free of dust, dirt, grease, oil or any other contaminants that may prevent proper adhesion. All loose paint must be removed and glossy surfaces dulled by sanding. Plaster surfaces must be well cured, and porous masonry surfaces should be filled with block filler. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Galvanized surfaces shall have all oils removed prior to application of coating.

Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

HALLMAN LINDSAY FINISHING RECOMMENDATIONS

Interior

High-Performance Acrylic: AQUAPOXY1 Series

Designer Finish: PURE and LUSTRE Series

Premium Finish: WONDERKOTE and EARTHSCAPES Series

Professional Finish: PRO KOTE and RENEWAL Series

Builder's Legacy Finishes: MASTER KOTE, VELVET ARMOR, and Premium Hi-Build Series

APPLICATION

Mix thoroughly before use. Apply by brush, roller, or airless spray or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Surfaces should be dry prior to paint application. For best filling of voids, apply by spray and backroll surface with $\frac{3}{4}$ " roller cover, pushing paint into voids. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with water immediately after use.

EQUIPMENT REQUIREMENTS

Airless: Minimum 1.20 GPM, 3000 PSI, .025-.029" Tip

HVLP: Not Recommended

Roller: $\frac{3}{4}$ " - 1" nap shed-resistant or lambswool cover

Brush: 100% Nylon or Synthetic Blend