



# PRO KOTE ZERO VOC

## SEMI-GLOSS INTERIOR LATEX WALL FINISH

### 296

PROFESSIONAL SERIES  
INTERIOR  
SEMI-GLOSS  
296  
PRO KOTE ZERO VOC

PROKOTE is a professional line of interior latex finishes designed for reliable, everyday performance. High-hiding and low-spatter features provide easier application for faster coverage, improved productivity, and faster job turnaround. MPI certified, LEED v4 compliant formulation delivers easy production application with outstanding touch-up ideal for commercial and institutional projects meeting the strictest air quality standards.

PROKOTE is designed to deliver easy and consistent results for the professional painter. The durable finish can be applied to drywall, plaster, wallboard, and other prepared surfaces. It is ideally suited for maintenance and new construction painting for commercial, institutional, and residential projects. May also be applied in light industrial facilities in non-corrosive

#### COMPLIANCE & CERTIFICATION

Gloss Level	4
VOC Content	3.761 g/L 0.03 lb./Gal
LEED v4 Credit Eligible	YES

#### RECOMMENDED USAGE

- For Interior Use
- Drywall, Plaster, Wallboard, and Similar Surfaces
- Maintenance and New Construction

#### PERFORMANCE & FEATURES

- Zero-VOC, LEED v4 Credit Eligible
- Easy Application
- Cost & Labor Savings
- Professional Interior Finish

#### BENEFITS

**Production Driven Performance:** High-hiding, sag and spatter resistant formula delivers quicker coverage for reduced labor and material costs.

**Versatile Application:** Easy brush, roll, and spray application with outstanding durability and touch-up provide value to professional painters during application and maintenance technicians for ongoing upkeep.

**Environmentally Responsible Finish:** Zero-VOC, LEED v4 Credit Eligible finish meets the performance needs of contractors, specifiers, property managers, and general contractors looking to meet the strictest air quality standards.

#### PRODUCT SPECIFICATIONS

**Vehicle Type:** Ethylene-Vinyl Acetate / Acrylic

**Color Tinting:** White. May be tinted, up to 2 oz. per gallon, with low VOC colorants.

**Gloss:** Semi-Gloss

35 units @ 60°

**Solid Content:** Weight: 44% ± 2

Volume: 33% ± 2

**Drying Time:** (75° F. & 50% R.H.)

To touch: 1 Hour

To recoat: 2 Hours

*Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc. are present. Allow product to dry thoroughly before top coating*

#### **Theoretical Coverage:**

Apply at 400 sq. ft./gal. to achieve

4.0 mils Wet Film Thickness

1.2 mils Dry Film Thickness

*When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.*

#### PRECAUTIONS/LIMITATIONS

- Please refer to Safety Data Sheets.
- Apply only if air, surface and material temperatures remain 50° F or above during application and drying.



# PRO KOTE ZERO VOC

## SEMI-GLOSS INTERIOR LATEX WALL FINISH

### 296

PROFESSIONAL SERIES  
INTERIOR  
SEMI-GLOSS  
296  
PRO KOTE ZERO VOC

#### **SURFACE PREPARATION**

Surfaces must be dry, clean and free of dust, dirt, grease, oil or any other contaminants that may prevent proper adhesion. All loose paint must be removed and glossy surfaces dulled by sanding. Plaster surfaces must be well cured, and porous masonry surfaces should be filled with block filler. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Galvanized surfaces shall have all oils removed prior to application of coating.

**Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-LEAD (5323) or log on to [www.epa.gov/lead](http://www.epa.gov/lead).**

#### **HALLMAN LINDSAY PRIMING RECOMMENDATIONS**

##### **New Work**

**Drywall:** Premium Wall Primer, 220.

**Plaster/Masonry:** GRIPCRETE Masonry/Plaster Primer, 166.

**Wood:** Enamel Undercoat, 231.

**Galvanized Surfaces:** Enamel Undercoat, 231, METALGUARD ACRYLIC DTM Primer/Finish, 338.

**Steel Surfaces:** METALGUARD Rust Inhibitive Primer, 330

**Block:** GRIPCRETE HD Block Filler, 181.

**Repaint:** Self-Priming (requires two coats).

#### **APPLICATION**

Mix thoroughly before use. Apply by brush, roller, or airless spray or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Do not brush or roll excessively. Surfaces should be dry prior to paint application. Reducing material for spray application should not exceed 10%. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with water immediately after use.

#### **EQUIPMENT REQUIREMENTS**

**Airless:** Minimum .70 GPM, 2500 PSI, .017-.019" Tip

**HVLP:** Twin-stage turbine, 5-8 PSI, .051 to .070 projector set

**Roller:** 1/2" - 3/4" nap synthetic cover

**Brush:** 100% Nylon or Synthetic Blend