



BUILDER'S LEGACY

PRO SMOOTH HI-BUILD

362

PERFORMANCE SERIES
INTERIOR
LO-SHEEN
362
PRO SMOOTH HI-BUILD

PRO SMOOTH HI-BUILD is a production high-build primer/finish formulated to prime, surface and finish drywall with a single product. Designed for coating new drywall, the higher film-build hides minor drywall imperfections and trade damage while producing an attractive, washable finish. Material and labor savings are achieved with increased speed and efficiency by applying the equivalent of three coats of traditional paint in a single pass.

PRO SMOOTH HI-BUILD is formulated to provide an economical single-source system for coating new drywall. This high building primer/finish is perfectly suited for residential, multi-family and commercial spaces looking for added savings and value. Designed for professional high-volume production, this product is intended for spray application only.

COMPLIANCE & CERTIFICATION

Gloss Level	4
VOC Content	53.14 g/L 0.36 lb./Gal

RECOMMENDED USAGE

- For Interior Use on New Drywall
- Efficient Spray Application
- Use in High-End Residential, Multi-Unit, Mixed-Use, and Commercial Construction

PERFORMANCE & FEATURES

- Cost & Labor Savings
- Single-Source System
- Low-Odor, Low-VOC
- Production Orientated Finish

BENEFITS

Production Finishing: Single-source system simplifies drywall finishing by eliminating the need for unique primer and finish product application.

Exceptional Hide: Provide savings by applying two coats to substrate to create a DFT greater than 4 coats of traditional primer/topcoat systems.

Minimize Impact: Low-odor, low-VOC, and containing no crystalline silicates, air quality impact is minimized on trades during application.

PRODUCT SPECIFICATIONS

Vehicle Type: Ethylene-Vinyl Acetate

Color Tinting: Pro White. May be tinted, up to 2 oz. per gallon, with low VOC colorants.

Gloss: Lo-Sheen

3-5 units @ 60°

8-10 units @ 85°

Solid Content: Weight: 56% ± 2

Volume: 38% ± 2

Drying Time: (75° F. & 50% R.H.)

To touch: 1 Hour

To recoat: Overnight

Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc. are present. Allow product to dry thoroughly before top coating

Theoretical Coverage:

Apply at 160 sq. ft./gal. to achieve

10.0 mils Wet Film Thickness

3.8 mils Dry Film Thickness

When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.

PRECAUTIONS/LIMITATIONS

- Please refer to Safety Data Sheets.
- Apply only if air, surface and material temperatures remain 50° F or above during application and drying.



BUILDER'S LEGACY

PRO SMOOTH HI-BUILD

362

PERFORMANCE SERIES
INTERIOR
LO-SHEEN
362
PRO SMOOTH HI-BUILD

SURFACE PREPARATION

Surfaces must be dry, clean and free of dust, dirt, grease, oil or any other contaminants that may prevent proper adhesion. All loose paint must be removed and glossy surfaces dulled by sanding. Plaster surfaces must be well cured, and porous masonry surfaces should be filled with block filler. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Galvanized surfaces shall have all oils removed prior to application of coating.

Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

HALLMAN LINDSAY PRIMING RECOMMENDATIONS

Drywall: Self-prime and finish (two coats required).

Plaster/Masonry: GRIPCRETE Masonry/Plaster Primer, 166.

Wood: Enamel Undercoat, 231.

Galvanized Surfaces: METALGUARD DTM Acrylic Primer/Finish, 338.

Steel Surfaces: METALGUARD Rust Inhibitive Primer, 330.

Block: GRIPCRETE Block Filler, 184.

APPLICATION

Mix thoroughly before use. Apply by airless spray for best results. May be applied by brush or roller; however, all properties related to hide and appearance may be affected. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Do not brush or roll excessively. Reducing material for spray application should not exceed 10%. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with water immediately after use.

EQUIPMENT REQUIREMENTS

Airless: Minimum .70 GPM, 3000 PSI, .019-.023" Tip

HVLP: Twin-stage turbine, 5-8 PSI, .051 to .070 projector set

Roller: 1/2"-1" nap synthetic cover

Brush: 100% Nylon or Synthetic Blend