



PROFESSIONAL
INTERIOR

KRILGUARD

Hallman Lindsay serves the communities where we live and work. We provide expertise and quality products made and mixed in Wisconsin for over 60 years.

GREAT PAINT. GREAT PEOPLE.



KRILGUARD

KRILGUARD is an interior professional grade multi-purpose enamel designed to provide a durable, fast drying finish on a variety of surfaces. Simplify maintenance painting and product schedules by using this single-source, all-in-one maintenance product for surfaces including lockers, handrails, and floors. The low-odor waterborne formula dries to the touch in 40 minutes minimizing downtime allowing for a faster return to service.

KRILGUARD'S unique waterborne formula provides a long lasting durable finish suitable for commercial and institutional application. Providing a hard, scrubbable finish allows for exceptional performance on interior surfaces including wood, drywall, metal doors and frames, and masonry surfaces. It is ideally suited for schools, healthcare facilities, and other areas requiring durable enamel finishes with minimal shutdown times.

FEATURES

- Single- Source Coating
- Outstanding Durability
- Minimal Shutdown Time
- Low-Odor Acrylic Enamel

BENEFITS

Multi-Purpose Enamel

Apply the same paint on trim, floors, cabinets, walls, and block will significantly streamline maintenance and simplify any stock room.

Fast Return to Service

Drying to the touch in less than hour allows for fast return to service minimizing shutdown time.

Sheen Availability

Available in all colors in a satin and gloss finish. Also available in an even faster drying spray-only version for faster stacking and shipping of trim packages.



TECHNICAL INFORMATION

BASES: SATIN - 316 SERIES • SEMI-GLOSS - X5681 SERIES • GLOSS - 317 SERIES

APPLICATION INFORMATION

Drying Time at 77° F 50% R.H:

To touch: 40 minutes

Recoat: 1 hour

Cure Time: 6 days

** Cooler temperatures and higher relative humidity will extend dry times*

Recommended Spreading Rate:

400 sq. ft./gal to achieve

4.0 mils Wet Film Thickness

1.8 mils Dry Film Thickness

Solids Content:

Volume: 45% ± 2 Weight: 58% ± 2

EQUIPMENT RECOMMENDATIONS

Roller: ¼" synthetic shed-resistant or mohair cover

Brush: 100% nylon or synthetic blend

Airless: Minimum ¾ GPM with .015" tip @ 2300-2700 PSI

HVLP: Twin-stage turbine, 5 – 8 PSI, .051 to .070 projector set

SAFETY AND COMPLIANCE

VOC (EPA Method 24):

105 g/L 0.88 lbs./Gal

PRIMER RECOMMENDATIONS

New Work

Drywall: Pro Wall Primer, 227.

Plaster/Masonry: Grip-Crete Masonry/Plaster Primer, 166.

Wood: Enamel Undercoat, 231.

Galvanized Surfaces: Enamel Undercoat, 231 or Metalguard DTM Acrylic Primer/Finish, 338.

Steel Surfaces: Metalguard Rust Inhibitive Primer, 330.

Block: Grip-Crete Block Kote Block Filler, 184.

Repaint: Self-Priming with two coats.