

PROFESSIONAL **EXTERIOR**

ALUMINUM KOTE



Hallman Lindsay serves the communities where we live and work. We provide expertise and quality products made and mixed in Wisconsin for over 60 years.

GREAT PAINT. GREAT PEOPLE.

**hallman
lindsay**
QUALITY PAINTS®

ALUMINUM KOTE

ALUMINUM KOTE is a premium ready-mix aluminum coating designed for professional application. This non-fibered coating provides a uniform, high-gloss aluminum finish. The leafing/flake aluminum formula creates an aluminum "barrier" providing maximum corrosion and heat resistance. The reflective coating helps reduce indoor temperatures for improved living and working conditions.

ALUMINUM KOTE is formulated specifically for commercial and agricultural uses. Providing a long-lasting and uniform finish, it can be used on a variety of surfaces including fences, poles, sign markers, structural steel, piping, machinery, equipment, and storage tanks. It can also be used as a maintenance roof coating over previously painted surfaces and other aluminum coatings. Not intended to be applied directly to bare galvanized surfaces.

FEATURES

- Bright Aluminum Coating
- High-Temperature Resistant
- Excellent Corrosion Resistance
- High-Gloss Finish

BENEFITS

Bright Aluminum Finish

Formulated with actual aluminum flake provides an extremely bright, reflective finish that reduces interior temperatures for improved living and working conditions.

Non-Fibered Finish

Protecting from corrosion, the overlapping flake blocks UV and moisture exposure preventing premature cracking and film breakdown.

High-Temperature Resistant

Unique adhesion allows for temperature exposure much higher than conventional coatings. Can handle surface temperatures of up to 250°F.



TECHNICAL INFORMATION

APPLICATION INFORMATION

Drying Time at 77° F 50% R.H:

To Touch: 2 hours*

Recoat: Overnight*

* Cooler temperatures and higher relative humidity will extend dry times

Recommended Spreading Rate:

550 sq. ft./Gal to achieve
3.0 mils Wet Film Thickness
1.3 Dry Film Thickness

Solids Content:

Volume: 42% ± 2 Weight: 51% ± 2

BASES: GLOSS - 320 SERIES

EQUIPMENT RECOMMENDATIONS

Roller: 1/4" - 1/2" nap synthetic shed-resistant or mohair cover

Brush: Natural china bristle or synthetic blend

Airless: Minimum ¾ GPM with .019" tip @ 2500-2700 PSI

HVLP: Twin-stage turbine, 5-8 PSI, .051- .070 projector set

SAFETY AND COMPLIANCE

VOC (EPA Method 24):

457 g/L 3.81 lbs./Gal

MPI Category: 1; Fed. Spec: TT-P-38E

PRIMING RECOMMENDATIONS

New Work

Wood Surfaces (Interior): Enamel Undercoat, 231.

Wood Surfaces (Exterior): Prime Kote, 111; Prime Guard, 112.

Rough Masonry/Concrete Block: Grip-Crete Surfacers, 179; Fill Kote HD Block Filler, 181.

Smooth Masonry/Brick: Grip-Crete Masonry/Plaster Primer, 166.

Metal, Ferrous: Metalguard, 330.

Metal, Non-Ferrous: Metalguard DTM Acrylic Primer/Finish, 338.

Repaint Surfaces: May be applied over existing coatings only after sample applications have been made to check the sensitivity of the existing coating. Surfaces must be primed and properly prepared if sensitivity or lifting occurs