



PREMIUM
EXTERIOR

METAL KOTE

Hallman Lindsay serves the communities where we live and work. We provide expertise and quality products made and mixed in Wisconsin for over 60 years.

GREAT PAINT. GREAT PEOPLE.

**hallman
lindsay**
QUALITY PAINTS®

METAL KOTE

METAL KOTE is a 100% acrylic exterior coating designed to minimize surface preparation and provide maximum adhesion and lasting color changes to metal siding. High acrylic resin content combined with rust-inhibitors creates a strong, corrosion-resistant bond to even weathered and lightly chalked surfaces. METAL KOTE is available in an attractive eggshell sheen that closely resembles factory pre-finished siding, allowing for greater uniformity between buildings.

METAL KOTE is designed to combat the challenges of recoating pre-finished and chalking metal siding. Stronger binders and corrosion resistance make it ideal for use on metal siding, windows, trim, and other prepared vertical surfaces. Can be applied to residential, commercial, agricultural, and light industrial buildings.

FEATURES

- Consistent Sheen
- Excellent Longevity
- Easy Application
- Soap & Water Clean-Up

BENEFITS

Cost & Labor Savings

Eliminate the need for paint additives and reduce surface preparation by applying directly over lightly chalking surfaces.

Lasting Protection

Premium 100% acrylic formulation provides strong adhesion, good flexibility with weather changes, and lasting color retention.

User-Friendly Application

High-hiding formula provides great coverage with brush, roller, and spray applications. Waterborne finish cleans easily with soap and water.



Easy Spray Application



Formulated for Metal Siding

TECHNICAL INFORMATION

APPLICATION INFORMATION

Drying Time at 77° F 50% R.H:

To Touch: 2 Hours*

Recoat: Overnight*

* Cooler temperatures and higher relative humidity will extend dry times

Recommended Spreading Rate:

320 sq. ft./ Gal to achieve
5.0 mils Wet Film Thickness
1.8 mils Dry Film Thickness

Solids Content:

Volume: 38% ± 3 Weight: 51% ± 3

BASES: EGGSHELL - 178 SERIES

EQUIPMENT RECOMMENDATIONS

Roller: ½" - 1" nap synthetic cover

Brush: 100% nylon or synthetic blend

Airless: Minimum ¼ GPM, .017" tip @ 2300-2500 PSI

Conventional: Binks #7 gun, 38 needle, 36 air nozzle, 38 fluid nozzle, 9.3 CFM @ 30 PSI

HVLP: Twin-stage turbine, 5 – 8 PSI, .051 to .070 projector set

SAFETY AND COMPLIANCE

VOC (EPA Method 24):

49 g/L 0.40 lbs./Gal

PRIMER RECOMMENDATIONS

Aluminum Siding: Self Priming (requires 2 coats) or Metalguard DTM Acrylic Primer/Finish, 338.

Galvanized Metal: Self Priming (requires 2 coats) or Metalguard DTM Acrylic Primer/Finish, 338.

Steel: Metalguard Rust Inhibitive Primer, 330.

CMU, Concrete Block and Split Face: Grip-Crete Heavy-Duty Block Filler, 181.

Masonry/Stucco: Self Priming or Grip-Crete Masonry/Plaster Primer, 166.

Wood Surfaces: Prime Kote, 111 for Cedar and Redwood. All other species Prime Guard, 112.