



DESIGNER
INTERIOR

LUSTRE

GREAT PAINT. GREAT PEOPLE.

SINCE 1956
**hallman
lindsay**
QUALITY PAINTS®

LUSTRE

LUSTRE is a Designer Quality Interior wall finish providing elegance and durability to fine homes and commercial offices. This high-end finish glides off the brush or roller with a rich silky appearance and buttery application reducing roller stipple and brush marks. This full-bodied formula is 100% acrylic offering a luxurious look and feel even after repeated washing. LUSTRE provides stain resistance allowing most blemishes to wipe off with soap and water or mild household detergent.

LUSTRE is formulated in Wisconsin for designer spaces with silky, smooth application qualities. The exceptional 100% acrylic resin durability is ideal for busy households, high traffic commercial offices and hospitality/event centers, as well as, hallways, baths, kitchens, and classrooms. Apply LUSTRE to enhance Designer Quality projects for a silky, smooth finish.

FEATURES

- 100% Acrylic Formula
- Silky Application
- Designer Coverage
- Exceptional Durability

BENEFITS

100% Acrylic Formula

The all-acrylic formula provides a premium scrubbable surface that repels stains, extending the life of the finish.

Silky Application

The silky, buttery application allows paint to glide off the brush and roller during application. This easy-to-apply finish produces a truly elegant appearance.

Faster Custom Colors

Designed for application and coverage, the high-hiding nature allows for faster color changes and blocking of previous coatings.



Exceptional Coverage

TECHNICAL INFORMATION

APPLICATION INFORMATION

Drying Time at 77° F 50% R.H:

To Touch: 1 hour*

Recoat: 4 hours*

* Cooler temperatures and higher relative humidity will extend dry times

Recommended Spreading Rate:

400 sq. ft./Gal to achieve
4.0 mils Wet Film Thickness
1.6 mils Dry Film Thickness

Solids Content:

Volume: 40% ± 2 Weight: 54% ± 2

BASES: LO-SHEEN - 280 SERIES • SATIN - 285 SERIES

EQUIPMENT RECOMMENDATIONS

Roller: ½" - ¾" nap synthetic cover

Brush: 100% nylon or synthetic blend

Airless: Minimum .50 GPM with .017-.019" tip @ 2600 PSI

HVLP: Twin-stage turbine, 5 – 8 PSI, .051 to .070 projector set

SAFETY AND COMPLIANCE

VOC (EPA Method 24):

41-124 g/L 0.34-1.03 lbs./Gal

MPI Category:

44, 43

PRIMER RECOMMENDATIONS

New Work

Drywall: Self-priming with two coats or Pro Wall Primer, 227.

Plaster/Masonry: Grip-Crete Masonry/Plaster Primer, 166.

Wood: Self-priming with two coats or Enamel Undercoat, 231.

Galvanized Surfaces: Self-priming with two coats or Metalguard DTM Acrylic Primer/Finish, 338.

Steel Surfaces: Metalguard Rust Inhibitive Primer, 330.

Block: Grip-Crete Block Kote Block Filler, 184.

Repaint: Self Priming (requires two coats).