



PRODUCT DATA SHEET

Builder's Legacy

Premium Series

Interior Drywall Primer/Sealer

WALL PREP PREMIUM WALL PRIMER/SEALER 220

DESCRIPTION

hallman/lindsay's Builders Legacy is our finest line of finishes designed for new drywall surfaces. All our **Builders Legacy** products meet LEEDS criteria for new construction.

Builder's Legacy WALL PREP PREMIUM WALL PRIMER is a latex interior wall primer with a high amount of resin. Provides for excellent sealing and finish painting for drywall, cured plaster and smooth masonry surfaces.

Suitable as a primer under a variety of finish products, 220 is highly suggested under higher gloss finishes such as epoxies and alkyd finishes.

Recommended for new construction and repaint in residential, multi-family, commercial, institutional and light industrial facilities.

FEATURES

- ✓ **Meets criteria set forth by the U.S. Green Building Council LEED-NC, version 2.2 and LEED-CI version 2.0.**
- ✓ Quick-Dry
- ✓ Excellent Sealing
- ✓ Outstanding Hold-Out
- ✓ Zero VOC per EPA Method 24
- ✓ **NOTE:** Material VOC content at or below 5g/L. This is based on an interpretation of the SCAQMD Rule 314 exemption for "Zero VOC equivalent" coatings.
- ✓ Low-Odor
- ✓ LEED v4 Certificate of Compliance for Emissions available upon request

PERFORMANCE DATA

- ✓ Performance alternate (MPI) Category # 50

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL DATA

- ✓ Color/Tinting:
White. May be tinted, up to 2 oz. per gallon, with low VOC universal colorants.
- ✓ Vehicle Type:
Ethylene-Vinyl Acetate
- ✓ Gloss: Flat
1-4 units @ 60°
- ✓ Percent Solids:
Weight: 42% ± 2
Volume: 28% ± 2
- ✓ Theoretical Coverage:
Apply at 400 sq.ft./gal. to achieve
4.0 mils Wet Film Thickness
1.1 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Drying Time at 77F° 50% R.H.:
To touch: 1 hour
Recoat: 4 hours
Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc are present. Allow product to dry thoroughly before topcoating.
- ✓ Thinning/Cleanup:
Water
- ✓ VOC (EPA Method 24):
0 g/L 0 lbs./gal

Products of Hallman/Lindsay Paints
Sun Prairie, WI 53590

9
Finishes
Painting (09900)

TECHNICAL SERVICES



FACTORY & MAIN OFFICES
Ph. 608/834-8844
Fax 608/837-1064
www.hallmanlindsay.com

SURFACE PREPARATION

On drywall, all taped joints and nail heads should be sanded smooth and dusted. Patch all holes and cracks with an appropriate patching compound. Let dry thoroughly, sand smooth and prime. Surfaces must be dry, clean and free of dirt, oil or any other contaminants. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

hallman/lindsay FINISH RECOMMENDATIONS

Choose any appropriate **hallman/lindsay** Earthscapes topcoat for Low-voc and low odor requirements.

May also be applied under any appropriate **hallman/lindsay** topcoat.

APPLICATION

Mix thoroughly before use. Apply by brush, roller, airless, HVLP or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Surfaces should be dry prior to paint application. Reducing material for spray application should not exceed 10%.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum ½ GPM with .017" tip @ 2000 PSI
- ✓ Conventional: Binks #7 gun, 38 needle, 36 air nozzle, 38 fluid nozzle, 9.3 CFM @ 30 PSI
- ✓ HVLP: Twin-stage turbine, 5–8 PSI, .051 to .070 projector set
- ✓ Roller: 3/8" – 3/4" nap shed-resistant cover or lambswool cover
- ✓ Brush: 100% nylon or synthetic blend



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.