



PREMIUM

**EXTERIOR**

**GRIPCRETE**  
100% ACRYLIC ELASTOMERIC

**GREAT PAINT. GREAT PEOPLE**



[hallmanlindsay.com](http://hallmanlindsay.com)

# 100% ACRYLIC ELASTOMERIC

100% ACRYLIC ELASTOMERIC is a professional grade 100% Acrylic Elastomeric coating created to protect and beautify exterior masonry surfaces. The 100% acrylic formulation has low-temperature flexibility and can elongate up to 300% to bridge moving hairline cracks. For maximum protection, apply up to 16 dry mils to produce a continuous, pinhole-free finish that protects from extended UV exposure and wind-driven rain.

100% ACRYLIC ELASTOMERIC is designed specifically for vertical masonry surfaces requiring flexibility and moisture protection. Ideally suited for exterior surfaces, it can be used for residential, commercial, and institutional new and repaint projects. Apply to a variety of prepared surfaces including wood, metal, and masonry surfaces such as EIFS, stucco, block, and tilt-up.

## FEATURES

- Wind-Driven Rain Protection
- Strong Adhesion
- Exceptional Elongation
- Low-Odor, Low-VOC

## BENEFITS

### Long Coating Lifecycle

The two-coat system provides 16 dry mils of long-lasting, pin-hole free weather and UV protection.

### Excellent Flexibility

Formulated to flex up to 300% elongation, this coating helps to bridge hairline cracks that expand and contract with Wisconsin seasonal changes.

### Self-Sealing Finish

When applied to prepared masonry, this high-building primer/finish has strong adhesion to split-face block, brick, stucco, and other highly porous surfaces.



SELF PRIMING ON CURED MASONRY



PINHOLE-FREE FINISH OVER POROUS SURFACES

## TECHNICAL INFORMATION

### APPLICATION INFORMATION

Drying Time at 77° F 50% R.H:

To Touch: 4 hours\*

Recoat: 24 hours\*

\* Cooler temperatures and higher relative humidity will extend dry times

Recommended Spreading Rate:

80 sq. ft./Gal to achieve 18 mils WFT; 8 mils DFT

Solids Content:

Volume: 45% ± 2 Weight: 56% ± 2

### BASES: EGGSHELL - 180 SERIES

### EQUIPMENT RECOMMENDATIONS

Roller: ¾" – 1¼" nap shed-resistant or lambswool cover

Brush: 100% nylon or synthetic blend

Airless: Minimum 1 GPM with .021" tip @ 2300-2500 psi

HVLP: Not recommended

### SAFETY AND COMPLIANCE

VOC (EPA Method 24):

30 g/L 0.25 lbs./Gal

### PRIMER RECOMMENDATIONS

Rough Masonry/Block: GRIPCRETE Block Surfer, 179 or GRIPCRETE HD Block Filler, 181.

Pre-Cast and Tilt-Up: GRIPCRETE Masonry & Plaster Primer, 166.

Wood Surfaces: PrimeKote, 111 for Cedar and Redwood. All other species PrimeGuard, 112.

Metal, Non-Ferrous: Metalguard DTM Acrylic Primer/Finish, 338.

Metal, Ferrous: Metalguard Rust Inhibitive Primer, 330.

Repaint Surfaces: Spot prime all bare areas with suitable primer.