

SEALZ-IT

INTERIOR/EXTERIOR ALKYD STAIN BLOCKING PRIMER

525

SEALZ-IT is a fast-drying alkyd primer/sealer formulated to prime and seal a variety of new and previously coated surfaces. Quick-dry solvents allow for finishing in as little as an hour for faster job completions. Alkyd resin system creates a strong seal to block out water stains, nicotine stains, tannins when spot priming exterior wood, and much more. Formulated to be a quick-fix solution to stains and priming needs, it is not intended to replace the benefits of premium and specialty primers.

Apply SEALZ-IT to lock-in stains and odors on a variety of new and previously painted surfaces' wood, plaster, drywall, hardboard, masonry, water-damaged walls, ceilings, trim, and other porous surfaces. May be used to prime surfaces prior to receiving vinyl wall coverings.

COMPLIANCE & CERTIFICATION

Gloss Level	1
VOC Content	408 g/L 3.40 lb./Gal

PERFORMANCE & FEATURES

- Quick Dry Solvent
- Stain Blocking Primer
- Easy Sanding
- Improved Coverage

BENEFITS

Quick Dry Alkyd: Solvent base allows for excellent blocking of stains including water damage, crayon, marker, and many others.

Easy Sand Formula: The easy sand feature makes it great for use on painted trim, molding, and cabinets.

High Hiding: The higher solids formulation provides great wet and dry hide giving a superb walk away appearance.

PRODUCT SPECIFICATIONS

Vehicle Type: Alkyd

Color Tinting: White. May be tinted, up to 4 oz. per gallon, with most universal colorants

Gloss: Flat

1-5 units @ 60°

Solid Content: Weight: 63% ± 2

Volume: 42% ± 2

Drying Time: (75° F. & 50% R.H.)

To touch: 30 Minutes

To recoat: 1 Hour

Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc. are present. Allow product to dry thoroughly before top coating

Theoretical Coverage:

Apply at 400 sq. ft./gal. to achieve

4.0 mils Wet Film Thickness

1.7 mils Dry Film Thickness

When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.

PRECAUTIONS/LIMITATIONS

- Please refer to Safety Data Sheets.
- Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

SURFACE PREPARATION

Surfaces must be dry, clean and free of dust, dirt, grease, oil or any other contaminants that may prevent proper adhesion. All loose paint must be removed and glossy surfaces dulled by sanding. Plaster surfaces must be well cured, and porous masonry surfaces should be filled with block filler. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Galvanized surfaces shall have all oils removed prior to application of coating.

Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

HALLMAN LINDSAY FINISHING RECOMMENDATIONS

Interior

Latex Finishes: Compatible with all Hallman Lindsay waterborne interior finishes.

Alkyd Finishes: Duraguard Series.

Exterior

Latex Finishes: Compatible with all Hallman Lindsay waterborne exterior finishes.

Alkyd Finishes: Duraguard Series.

APPLICATION

Mix thoroughly before use. Apply by brush, roller, or airless spray or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Do not brush or roll excessively. Surfaces should be dry prior to paint application. Reducing material for spray application should not exceed 10%. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with mineral spirits immediately after use.

EQUIPMENT REQUIREMENTS

Airless: Minimum .50 GPM, 2600 PSI, .015-.019" Tip

HVLP: Twin-stage turbine, 5 – 8 PSI, .051 to .070 projector set

Roller: 1/2" - 3/4" nap synthetic cover

Brush: Natural China Bristle or Synthetic Blend