



PREMIUM

EXTERIOR

GRIPCRETE
VERTICAL CONCRETE STAIN

GREAT PAINT. GREAT PEOPLE

SINCE 1956
**hallman
lindsay**
QUALITY PAINTS®

hallmanlindsay.com

VERTICAL CONCRETE STAIN

GRIPCRETE VERTICAL CONCRETE STAIN is a 100% acrylic concrete stain designed for easy application while improving aesthetics of exterior vertical concrete surfaces. Specifically formulated as a water-repellent coating, the opaque finish has high alkali and efflorescence resistance. Reduce labor and material costs by eliminating specialty primers with this self-priming, pH-tolerant (7-13) coating. This self-priming finish will increase efficiencies by providing a finished system in as little as two coats versus traditional three coat systems.

GRIPCRETE VERTICAL CONCRETE STAIN is designed specifically for vertical, non-porous cementitious surfaces where alkali and efflorescence resistance is required. This product is best used on new and unsealed tilt-up, precast, poured concrete, CMU, and stucco surfaces.

FEATURES

- Breathable Acrylic Coating
- Extended Color Retention
- Cost & Labor Saving System
- Warrantied Protection Available

BENEFITS

Breathable Exterior Coating

100% acrylic resin produces a breathable film that helps interior moisture pass through the coating without peeling or chipping.

Natural Appearance

Formulated with a flat finish to hide inconsistencies in masonry work while providing extended color retention.

Improved Finishing Timeline

Alkali and efflorescence resistant technology adds material and labor savings by eliminating the need for specialty primers.

System Warranty Available

Upon inspection and pre-application approval, system warranty is available. Some limitations apply, Consult your Hallman Lindsay representative for details.



TECHNICAL INFORMATION

APPLICATION INFORMATION

Drying Time at 77° F 50% R.H:

To Touch: 30 Minutes

Recoat: 30 Minutes

* Cooler temperatures and higher relative humidity will extend dry times

Recommended Spreading Rate:

150-250 sq. ft./Gal

Solids Content:

Volume: 30% ± 2 Weight : 46% ± 2

BASES: WHITE - 167 SERIES

EQUIPMENT RECOMMENDATIONS

Roller: 3/8" to 1/2" nap synthetic cover

Brush: 100% nylon or synthetic blend

Airless: Minimum 1 GPM airless with 3/8" hose and .017-.021" tip, 2000 PSI

SAFETY AND COMPLIANCE

VOC (EPA Method 24):

49 g/L 0.41 lbs./Gal

FINISHING RECOMMENDATIONS

Rough Masonry Surfaces: Self-priming, (requires two coats); GRIPCRETE BLOCK SURFACER, 179; GRIPCRETE MASONRY PLASTER & PRIMER, 166.

Smooth Masonry Surfaces: GRIPCRETE MASONRY PLASTER & PRIMER, 166.

Stucco, Tilt-up, Pre-Cast: Self-priming (requires two coats); GRIPCRETE MASONRY PLASTER & PRIMER, 166.