



DESIGNER

EXTERIOR

TIMBERSHADES
SOLID OPAQUE ACRYLIC STAIN



GREAT PAINT GREAT PEOPLE

SINCE 1956
**hallman
lindsay**
QUALITY PAINTS®

hallmanlindsay.com

TIMBERSHADES

TIMBERSHADES SOLID OPAQUE ACRYLIC STAIN is a designer quality 100% acrylic opaque wood stain that provides long lasting color and weather protection on exterior siding. Formulated using the same thixotropic technology as our other exterior products enables easy pickup and release from the brush for faster and cleaner application.

TIMBERSHADES SOLID OPAQUE ACRYLIC STAIN's high hiding acrylic formula provides a flexible coating with excellent UV protection perfect for Wisconsin's seasonal changes. The 100% acrylic formula of TIMBERSHADES SOLID OPAQUE ACRYLIC STAIN makes it a fantastic maintenance stain that is flexible, resists fading and will never chalk. Best suited for use on vertical previously stained shake, siding, fencing, and most hardboard surfaces.

FEATURES

- Easy Brushability
- Advanced Color Protection
- Mildew Resistant
- Strong Adhesion

BENEFITS

Advanced Color Protection

The 100% acrylic formula produces outstanding adhesion, color retention and flexibility that will resist mildew, fade, peeling, and blistering.

Clean & Easy Application

Thixotropic technology creates a thick, hearty feel yet the stain still glides off the brush. The "drip-less" advantage helps to cut back on drips and runs in your finish with less fatigue.

Excellent Appearance

This full bodied stain provides a rich appearance that will not leave the wood looking dry and dull.



TECHNICAL INFORMATION

APPLICATION INFORMATION

Drying Time at 77° F 50% R.H:

To Touch: 2 hours*; Recoat: 4 hours*

* Cooler temperatures and higher relative humidity will extend dry times

Application Temperature:

Apply Down to 35° F. Ask for details.

Recommended Spreading Rate:

400 sq. ft./gal to achieve
4.0 mils WFT; 1.3 mils DFT

Solids Content:

Volume: 36% ± 2 Weight: 53% ± 2

BASES: FLAT - 185 SERIES

EQUIPMENT RECOMMENDATIONS

Roller: ½" - ¾" nap synthetic cover

Brush: 100% nylon or synthetic blend

Airless: Minimum ¾ GPM with .017" tip
@ 2000 PSI

HVLP: Not recommended

SAFETY AND COMPLIANCE

VOC (EPA Method 24):

62 g/L 0.52 lbs./Gal

PRIMING RECOMMENDATIONS

Wood Surfaces: Self-priming. For best results prime with PRIME KOTE, 111 for Cedar and Redwood. All other species optional PRIMEGUARD, 112.

Aluminum: Self Priming (requires 2 coats) or ACRYLIC DTM Primer/Finish, 338.

Galvanized Metal: Self Priming (requires 2 coats) or ACRYLIC DTM Primer/Finish, 338.

Steel: METALGUARD QD Rust-Inhibitive Primer, 330.

CMU, Concrete Block and Split Face: GRIPCRETE Masonry Surfer, 179.

Masonry/Stucco: Self Priming or GRIPCRETE Masonry/Plaster Primer, 166.